

# TECAFIL PEEK VX black - 1.75 mm - Filament

## Chemical Designation

PEEK (Polyetheretherketone)

## Colour

black opaque

## Density

1.3 g/cm<sup>3</sup> (\*2)

## Main features

- inherent flame retardant
- very good chemical resistance
- good slide and wear properties
- good heat deflection temperature
- resistance against high energy radiation
- hydrolysis and superheated steam resistant

## Target Industries

- electronics
- food technology
- automotive industry
- chemical technology
- mechanical engineering
- aircraft and aerospace technology

## General material information

|                           | parameter      | value         | unit | norm | comment  |
|---------------------------|----------------|---------------|------|------|--|
| Diameter                  |                | 1,75 +/- 0,05 | mm   | -    |  |
| Spool measurements        | holder         | Ø 52          | mm   | -    | (1) standard spool body<br>(2) do not dry spool >120°C<br>(3) Ø 1,75mm |
| Spool measurements        | width          | 55            | mm   | -    |  |
| Spool measurements        | outer diameter | Ø 200         | mm   | -    | 1)   |
| Spool Material            |                | Polycarbonate |      | -    | 2)   |
| Filament Load per Spool   |                | 500           | g    | -    |  |
| Filament Length per Spool |                | 149           | m    | -    | 3)   |

## Mechanical properties

|                                      | parameter               | value  | unit | norm             | comment |
|--------------------------------------|-------------------------|--------|------|------------------|---------|
| Tensile strength                     | 5mm/min, Orientation XY | 84,4   | MPa  | DIN EN ISO 527-2 | 1)      |
| Tensile strength                     | 5mm/min, Orientation XZ | 94,8   | MPa  | DIN EN ISO 527-2 | 2)      |
| Tensile strength                     | 5mm/min, Orientation ZX | 85,6   | MPa  | DIN EN ISO 527-2 | 3)      |
| Modulus of elasticity (tensile test) | 5mm/min, Orientation XY | 3365,0 | MPa  | DIN EN ISO 527-2 | 4)      |
| Modulus of elasticity (tensile test) | 5mm/min, Orientation XZ | 3950,0 | MPa  | DIN EN ISO 527-2 | 5)      |
| Modulus of elasticity (tensile test) | 5mm/min, Orientation ZX | 3700,8 | MPa  | DIN EN ISO 527-2 | 6)      |
| Elongation at yield (tensile test)   | 5mm/min, Orientation XY | 6,5    | %    | DIN EN ISO 527-2 | 7)      |
| Elongation at yield (tensile test)   | 5mm/min, Orientation XZ | 6,7    | %    | DIN EN ISO 527-2 | 8)      |
| Elongation at yield (tensile test)   | 5mm/min, Orientation ZX | 4,5    | %    | DIN EN ISO 527-2 | 9)      |
| Elongation at break (tensile test)   | 5mm/min, Orientation XY | 29,9   | %    | DIN EN ISO 527-2 | 10)     |
| Elongation at break (tensile test)   | 5mm/min, Orientation XZ | 17,7   | %    | DIN EN ISO 527-2 | 11)     |
| Elongation at break (tensile test)   | 5mm/min, Orientation ZX | 5,0    | %    | DIN EN ISO 527-2 | 12)     |

## Thermal properties

|                              | parameter  | value | unit                             | norm                 | comment        |
|------------------------------|------------|-------|----------------------------------|----------------------|----------------|
| Glass transition temperature |            | 143   | °C                               | ASTM D 3418          | 1)             |
| Melting temperature          |            | 343   | °C                               | DIN EN ISO 11357     | 2)<br>(3) (*2) |
| Deflection temperature       | HDT-A      | 162   | °C                               | ISO-R 75 Method A    | 3)<br>(4) (*2) |
| Service temperature          | short term | 300   | °C                               | -                    | 5)<br>(6) (*2) |
| Service temperature          | long term  | 260   | °C                               | -                    |                |
| Thermal expansion (CLTE)     |            | 5     | 10 <sup>-5</sup> K <sup>-1</sup> | DIN EN ISO 11359-1;2 | 6)             |

## Other properties

|                       | parameter    | value | unit     | norm                 | comment        |
|-----------------------|--------------|-------|----------|----------------------|----------------|
| Moisture absorption   |              | 0,03  | %        | DIN EN ISO 62        | 1)<br>(2) (*2) |
| Flammability (UL94)   | 125x13x1,5mm | V0    |          | DIN IEC 60695-11-10; | 2)<br>(3) (*2) |
| Melt flow index (MFI) | 380°C / 5kg  | 8     | g/10 min | DIN EN ISO 1133      | 3)             |

## Processing parameter

|                           | parameter | value     | unit | norm | comment      |
|---------------------------|-----------|-----------|------|------|--------------|
| Nozzle temperature        |           | 420 - 440 | °C   | -    | (1) required |
| Max. melt temperature     |           | 470       | °C   | -    |              |
| Print bed temperature     |           | 160 - 250 | °C   | -    |              |
| Build chamber temperature |           | 160 - 230 | °C   | -    | 1)           |
| Nozzle diameter           |           | 0,4       | mm   | -    |              |
| Print speed               |           | 20 - 30   | mm/s | -    |              |
| Fan speed                 |           | 0         | %    | -    |              |

## Predrying

|                    | parameter | value | unit | norm | comment        |
|--------------------|-----------|-------|------|------|----------------|
| Drying temperature |           | 120   | °C   | -    | 1)<br>(1) (*4) |
| Drying time        |           | 8     | h    | -    |                |