


## Product Information

## VESTAMID® Care ML17

## LOW VISCOSITY POLYAMIDE 12 FOR MEDICAL APPLICATION



**VESTAMID® Care ML17** is resistant to body fluids and toxicologically safe.

Typical application areas for filled VESTAMID Care ML grades include catheters, housing parts, monitoring and imaging devices and durable medical equipment.

**The advantages at a glance:**

- High flexibility & elasticity
- Good rebound properties
- High impact resistance
- Excellent dimensional stability
- High chemical resistance
- Easy processability & colorability
- Plasticizer-free
- Gamma and EtO sterilization resistant
- Tough and resilient

**Biocompatibility of VESTAMID® Care ML**

Biocompatibility was tested following ISO10993-1 recommendations for a surface medical device with up to 30 days body contact.

The material fulfills the requirements of USP<88> class VI.

Tests were performed by independent, certified laboratories.

**Biocompatibility tests for VESTAMID® Care:**

| Standard     | Description                                                           |
|--------------|-----------------------------------------------------------------------|
| ASTM F756-08 | Hemocompatibility                                                     |
| ISO 10993-5  | Cytotoxicity                                                          |
| ISO 10993-10 | Sensitization: Maximization test according to Magnusson and Kligman   |
| ISO 10993-10 | Irritation: Intracutaneous Reactivity                                 |
| ISO 10993-11 | Acute Systemic Toxicity                                               |
| USP Class VI | Acute Systemic Toxicity Intracutaneous Reactivity Muscle Implantation |

**Processing of VESTAMID® Care**

For information about processing of VESTAMID®, please follow the general commendations about "[Processing of VESTAMID® compounds](#)".

The values presented are typical or average values, they do not constitute a specification.

## Key Features

### Industrial Sector

Sustainable, Medical Devices

### Sustainability

Sustainable electricity

### Processing

Injection molding

### Delivery form

Pellets, Granules

### Optics

Translucent

### Conformity

Biocompatibility, Medical application

### Additives

Unfilled

## LCA-values

|                                                 | dry                           | Unit                      | Test Standard    |
|-------------------------------------------------|-------------------------------|---------------------------|------------------|
| LCA name of certificate                         | <a href="#">VESTAMID® L</a>   | -                         | ISO 14040, 14044 |
| LCA certifier                                   | <a href="#">TÜV Rheinland</a> | -                         | ISO 14040, 14044 |
| Blue water consumption                          | <b>14.4</b>                   | kg                        | ISO 14040, 14044 |
| Global Warming Potential incl. bio. C incl. LUC | <b>5.8</b>                    | kg CO <sub>2</sub> eq./kg | ISO 14040, 14044 |
| Global Warming Potential excl. bio. C incl. LUC | <b>5.8</b>                    | kg CO <sub>2</sub> eq./kg | ISO 14040, 14044 |
| Land use (ReCiPe 2016)                          | <b>0</b>                      | Annual crop eq. y         | ISO 14040, 14044 |
| GWP savings as compared to 2023 reference       | <b>-1.3</b>                   | kg CO <sub>2</sub> eq./kg | ISO 14040, 14044 |

## Mechanical properties ISO

|                               | dry / cond         | Unit              | Test Standard |
|-------------------------------|--------------------|-------------------|---------------|
| Tensile modulus               | <b>1400 / 1120</b> | MPa               | ISO 527       |
| Tensile strength              | <b>43 / 41</b>     | MPa               | ISO 527       |
| Yield stress                  | <b>43 / 41</b>     | MPa               | ISO 527       |
| Yield strain                  | <b>5 / 13</b>      | %                 | ISO 527       |
| Stress at 50% strain          | <b>31 / 31</b>     | MPa               | ISO 527       |
| Stress at break               | <b>58 / 32</b>     | MPa               | ISO 527       |
| Nominal strain at break, tB   | <b>320 / 40</b>    | %                 | ISO 527       |
| Charpy impact strength, +23°C | <b>N / N</b>       | kJ/m <sup>2</sup> | ISO 179/1eU   |
| Charpy impact strength, -30°C | <b>N / 50</b>      | kJ/m <sup>2</sup> | ISO 179/1eU   |
| Type of failure               | <b>- / C(N)</b>    | -                 | -             |

|                                            |                    |                   |             |
|--------------------------------------------|--------------------|-------------------|-------------|
| Charpy impact strength, -40°C              | <b>N / -</b>       | kJ/m <sup>2</sup> | ISO 179/1eU |
| Charpy notched impact strength, +23°C      | <b>4.5 / 4.5</b>   | kJ/m <sup>2</sup> | ISO 179/1eA |
| Type of failure                            | <b>C / C</b>       | -                 | -           |
| Charpy notched impact strength, -30°C      | <b>6 / 5</b>       | kJ/m <sup>2</sup> | ISO 179/1eA |
| Type of failure                            | <b>C / C</b>       | -                 | -           |
| Charpy notched impact strength, -40°C      | <b>6 / -</b>       | kJ/m <sup>2</sup> | ISO 179/1eA |
| Type of failure                            | <b>C / -</b>       | -                 | -           |
| Flexural modulus, 23°C                     | <b>1430 / 1120</b> | MPa               | ISO 178     |
| Flexural stress at conv. deflection, 23°C  | <b>47 / 35</b>     | MPa               | ISO 178     |
| Flexural strength, 23°C                    | <b>58 / 48</b>     | MPa               | ISO 178     |
| Flexural strain at flexural strength, 23°C | <b>7 / 8</b>       | %                 | ISO 178     |

| <b>Thermal properties</b>                                  | <b>dry / cond</b> | <b>Unit</b> | <b>Test Standard</b> |
|------------------------------------------------------------|-------------------|-------------|----------------------|
| Melting temperature                                        | <b>178 / *</b>    | °C          | ISO 11357-1/-3       |
| Glass transition temperature, DSC                          | <b>45 / *</b>     | °C          | ISO 11357-1/-2       |
| Temp. of deflection under load A, 1.80 MPa                 | <b>50 / *</b>     | °C          | ISO 75-1/-2          |
| Temp. of deflection under load B, 0.45 MPa                 | <b>110 / *</b>    | °C          | ISO 75-1/-2          |
| Vicat softening temperature A, 10 N, 50 K/h                | <b>170 / *</b>    | °C          | ISO 306              |
| Vicat softening temperature B, 50 N, 50 K/h                | <b>140 / *</b>    | °C          | ISO 306              |
| Coeff. of linear therm. expansion, 23°C to 55 °C, parallel | <b>150 / *</b>    | E-6/K       | ISO 11359-1/-2       |
| Melting Temperature                                        | <b>178</b>        | °C          | ASTM D 3418          |

| <b>Physical properties</b> | <b>dry / cond</b>           | <b>Unit</b>       | <b>Test Standard</b> |
|----------------------------|-----------------------------|-------------------|----------------------|
| Density                    | <b>1020 / -</b>             | kg/m <sup>3</sup> | ISO 1183             |
| Water absorption           | <b>1.5 / *</b>              | %                 | Sim. to ISO 62       |
| Humidity absorption        | <b>0.7 / *</b>              | %                 | Sim. to ISO 62       |
| Shore D hardness           | <b>75<sup>[b]</sup> / -</b> | -                 | ISO 7619-1           |
| Density                    | <b>1020</b>                 | kg/m <sup>3</sup> | ASTM D 792           |

b: 3 seconds

| <b>Burning Behav.</b>                 | <b>dry / cond</b> | <b>Unit</b> | <b>Test Standard</b> |
|---------------------------------------|-------------------|-------------|----------------------|
| Burning behav. at 1.5 mm nom. thickn. | <b>HB / *</b>     | class       | IEC 60695-11-10      |
| Thickness tested                      | <b>1.6 / *</b>    | mm          | -                    |
| Burnin behav. at thickness h          | <b>HB / *</b>     | class       | IEC 60695-11-10      |
| Thickness tested                      | <b>3.2 / *</b>    | mm          | -                    |

| <b>Electrical properties</b>                | <b>dry / cond</b>          | <b>Unit</b>    | <b>Test Standard</b> |
|---------------------------------------------|----------------------------|----------------|----------------------|
| Volume resistivity, V                       | <b>&gt;1E13 / 2.3E12</b>   | Ohm*m          | IEC 62631-3-1        |
| Surface resistivity, C, circular electrodes | <b>&gt;1E15 / &gt;1E15</b> | Ohm per square | IEC 62631-3-2        |
| Relative permittivity, 50Hz                 | <b>3.9 / -</b>             | -              | IEC 62631-2-1        |
| Relative permittivity, 100Hz                | <b>3.8 / -</b>             | -              | IEC 62631-2-1        |
| Relative permittivity, 1MHz                 | <b>2.9 / -</b>             | -              | IEC 62631-2-1        |
| Dissipation factor, 100Hz                   | <b>500 / -</b>             | E-4            | IEC 62631-2-1        |
| Dissipation factor, 1MHz                    | <b>281 / -</b>             | E-4            | IEC 62631-2-1        |
| Dielectric strength, AC, S20/P50            | <b>26 / -</b>              | kV/mm          | Sim. to IEC 60243-1  |

| <b>Rheological properties</b> | <b>dry / cond</b> | <b>Unit</b>            | <b>Test Standard</b> |
|-------------------------------|-------------------|------------------------|----------------------|
| Melt volume-flow rate, MVR    | <b>21 / *</b>     | cm <sup>3</sup> /10min | ISO 1133             |
| Temperature                   | <b>210 / *</b>    | °C                     | -                    |
| Load                          | <b>2.16 / *</b>   | kg                     | -                    |
| Molding shrinkage, parallel   | <b>0.7 / *</b>    | %                      | ISO 294-4, 2577      |
| Molding shrinkage, normal     | <b>1.2 / *</b>    | %                      | ISO 294-4, 2577      |
| Mold temperature              | <b>60 / *</b>     | °C                     | -                    |
| Melt temperature              | <b>210 / *</b>    | °C                     | -                    |

| <b>Test specimen production</b>     | <b>dry</b> | <b>Unit</b> | <b>Test Standard</b> |
|-------------------------------------|------------|-------------|----------------------|
| Injection Molding, melt temperature | <b>210</b> | °C          | ISO 294              |
| Injection Molding, mold temperature | <b>60</b>  | °C          | ISO 294              |

Injection Molding, injection velocity

**200**

mm/s

ISO 294

## Characteristics

### Applications

Encapsulation, Tube and hose

### Special Characteristics

Low viscosity

### Features

Low coefficient of friction

### Regulatory

US Pharmacopeia Class VI conformity

### Color

Natural color

### Chemical Resistance

General chemical resistance