

Polyetheretherketone  
with PTFE, lubricant modified, easy flowing, graphite grey

Physical properties		Test method	Specimen	Units	Typical value
Specific gravity		ISO 1183-3		g/cm <sup>3</sup>	1,55
Water absorption	23°C / 24h	ISO 62	ISO 3167 A	%	<0,1
Linear mould shrinkage		DIN 16742	ISO 3167 A	%	0,7-1,2
Flammability behaviour		UL 94	1/16"		(V-0)

#### Mechanical properties at 23°C / 50% rh

Tensile strength	dry, @50 mm/min	ISO 527	ISO 3167 A	MPa	80
Elongation @Fmax.	dry, @50 mm/min	ISO 527	ISO 3167 A	%	3,3
Tensile modulus	dry, @1 mm/min	ISO 527	ISO 3167 A	GPa	4
Flexural strength	dry, @10 mm/min	ISO 178	ISO 3167 A	MPa	105
Flexural elongation @Fmax.	dry, @10 mm/min	ISO 178	ISO 3167 A	%	4,4
Flexural modulus	dry, @2 mm/min	ISO 178	ISO 3167 A	GPa	3,4
Impact strength	dry	ISO 179 1eU	80x10x4mm	kJ/m <sup>2</sup>	32

#### Thermal properties

Continuous service temp.	20.000 h	IEC 60216	ISO 3167 A	°C	250
Service temperature	during lifetime max. 200h		ISO 3167 A	°C	260
CLTE, longitudinal		ISO 11359	10x8x4 mm	10 <sup>-5</sup> /K	5

#### Tribological properties

CoF - Block on Ring	100Cr6, 1 MPa, 1 m/s	ASTM G137	molded sample		0,40
Sp. Wear Rate-Block on Ring	100Cr6, 1 MPa, 1 m/s	ASTM G137	molded sample	10 <sup>-6</sup> mm <sup>3</sup> /Nm	2
Sp. Wear Rate-Block on Ring	100Cr6, 1 MPa, 2 m/s	ASTM G137	molded sample	10 <sup>-6</sup> mm <sup>3</sup> /Nm	2

#### Main features

Improved friction and wear behaviour. Optimised for dry running operations. Chemically- and hydrolytically- resistant parts, non flammable. Dynamically-stressed parts moving at high velocity. High dimensionally stable precision parts.

Polyetheretherketone  
with PTFE, lubricant modified, easy flowing, graphite grey

## Recommended processing parameters

### Delivery form & storage

Unless indicated otherwise, the material is delivered as 3mm long pellets in sealed bags on pallets. Preferably storage should be effected in dry and normally temperatured rooms.

### Predrying

It is advisable to predry the granules with a suitable dryer immediately before processing. The granule may absorb moisture from the environment.

Dryer type	Temperature °C	Drying time in h
Dehumidifying dryer	150	3 - 6
or	120	6 - 8

### Recommended processing parameters

In general this product can be processed on conventional injection moulding machines while observing the usual technical guidelines. Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials. Lengthy dwell times for the melts in the cylinder should be avoided. Lower the temperatures during interruptions!

Mold	Melt temperature	Nozzle	Zone 3	Zone 2	Zone 1
170 - 200 °C	390 °C	360 - 380 °C	390 - 400 °C	380 - 390 °C	360 - 370 °C

### Additional information

During processing, the moisture content should not exceed 0.05%. To avoid internal stresses, a medium to high injection rate should be used. An increase in tool temperature may be helpful. Post-crystallization may lead to warpage at elevated operating temperatures. This can be counteracted by suitable heat treatment. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. High-temperature polymers place increased demands on the tool steels employed. Please contact us for further information.