

VICTREX™ PEEK POLYMER 90HMF20

General Information

Product Description

High performance thermoplastic material, 20% carbon fibre reinforced PolyEtherEtherKetone (PEEK), semi crystalline, granules for injection moulding, very easy flow, colour black.

Complex geometries with thinner cross sections or longer flow length where superior strength in a static or dynamic system is required. Excellent wear resistance, low coefficient of friction, low coefficient of thermal expansion. Chemically resistant to aggressive environments.

Material Properties

Physical	Nominal Value	Unit	Test Method
Density (Crystalline)	1.37	g/cm ³	ISO 1183
Spiral Flow ¹	18.0	cm	Internal Method
Molding Shrinkage ²			ISO 294-4
Across Flow	0.60	%	
Flow	0.0	%	
Water Absorption (Saturation, 23°C)	0.40	%	ISO 62
Water Absorption Saturation (100°C)	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	22000	MPa	ISO 527-1
Tensile Stress			ISO 527-2
Break, 23°C	290	MPa	
Break, 125°C	190	MPa	
Break, 175°C	120	MPa	
Break, 275°C	80.0	MPa	
Tensile Strain (Break, 23°C)	1.9	%	ISO 527-2
Flexural Modulus (23°C)	20000	MPa	ISO 178
Flexural Stress			ISO 178
23°C	400	MPa	
125°C	290	MPa	
175°C	180	MPa	
275°C	100	MPa	
Compressive Stress			ISO 604
23°C	270	MPa	
120°C	200	MPa	
200°C	90.0	MPa	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	60.0	kJ/m ²	ISO 179/1U
Notched Izod Impact Strength (23°C)	8.5	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength (23°C)	60.0	kJ/m ²	ISO 180
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 23°C)	86.5		ISO 868

VICTREX™ PEEK POLYMER 90HMF20

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	347	°C	ISO 75-2/Af
Glass Transition Temperature (Onset)	143	°C	ISO 11357-2
Melting Temperature	343	°C	ISO 11357-3
CLTE - Flow			ISO 11359-2
> 143°C	3	ppm/K	
< 143°C	6	ppm/K	
CLTE - Average			ISO 11359-2
< 143°C	40	ppm/K	
> 143°C	100	ppm/K	
Thermal Conductivity			ISO 22007-4
23°C ³	1.0	W/m/K	
23°C ⁴	1.9	W/m/K	

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ⁵ (23°C)	1.0E+5	ohms·cm	ASTM D4496

Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (400°C)	175	Pa·s	ISO 11443

Typical Processing Information

Injection	Nominal Value	Unit
Drying Temperature	120 to 150	°C
Drying Time	3.0 to 5.0	hr
Hopper Temperature	< 100	°C
Rear Temperature	365	°C
Middle Temperature	370 to 375	°C
Front Temperature	380	°C
Nozzle Temperature	385	°C
Mould Temperature	180 to 200	°C

Injection Notes
Runner: Die / nozzle >3mm, manifold >3.5mm
Gate: >2mm or 0.5 x part thickness

Notes

¹ Mould Temperature: 190°C, Melt Temperature: 385°C, 1.00 mm

² 385°C nozzle, 190°C tool

³ Average

⁴ Along flow

⁵ 1V