



SABIC® PP 412MN40

PP block copolymer for Injection moulding

Description:

A multi-purpose grade with very good flow properties, high stiffness and good impact strength. The material has a very low tendency for warpage and is suited for the production of thin wall packaging articles. Cycle times can be very short. It is formulated with a combined processing and antistatic additive package. This grade is widely applied in thin wall technical injection moulded articles and thin-walled containers, in particular where dimensional stability is important.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site
<http://www.SABIC-europe.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 (www.ul.com) / IMDS 80775790

Typical values


Revision 20140109

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	g/10 min	37	ASTM D 1238
Density	kg/m³	905	ASTM D 792
Formulation			
Anti static agent	-	Yes	-
Nucleating agent	-	No	-
Mechanical properties			
Tensile test			ASTM D 638
stress at yield ¹⁾	MPa	25	
strain at yield ¹⁾	%	5	
secant modulus at 1% elongation ²⁾	MPa	1400	
Izod impact notched			ASTM D 256A
at 23 °C	J/m	90	
at 0 °C	J/m	65	
at -20 °C	J/m	55	
Rockwell hardness			ASTM D 785
R-scale	-	95	
Thermal properties			
Heat deflection temperature			ASTM D 648
at 1.80 MPa (HDT/A)	°C	60	
at 0.45 MPa (HDT/B)	°C	90	
Vicat softening temperature ³⁾			
at 10 N (VST/A)	°C	150	ASTM D 1525
at 50 N (VST/B)	°C	75	

1) Speed of testing: 50 mm/min

2) Speed of testing: 5 mm/min

3) Temperature rate: 120°C/h



SABIC® PP 412MN40

PP block copolymer for Injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.