



SABIC® PP 4935

PP random for Automotive injection moulding

Description:

SABIC® PP 4935 is a random copolymer with a very high molecular weight. This grade has a special stabilization package. The stabilization and particular molecular structure make it suited for use in extremely demanding applications like coolant expansion vessels in cars. The grade can be processed by injection molding. The material has a medium impact, is semi-transparent and has a good stress-whitening (low blushing) characteristic.

IMDS ID: 80775790

Typical values

Revision 20140109

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	g/10 min	0.3	ASTM D 1238
Density	kg/m ³	905	ASTM D 792
Mould shrinkage ¹⁾ 24 hours after injection moulding	%	1.9	SABIC method
Formulation			
Clarified	-	No	-
Anti static agent	-	No	-
Mechanical properties			
Tensile test			ASTM D 638
stress at yield ²⁾	MPa	22	
strain at yield ²⁾	%	6	
secant modulus at 1% elongation ³⁾	MPa	1350	
Izod impact notched			ASTM D 256A
at 23 °C	J/m	400	
at 0 °C	J/m	25	
at -20 °C	J/m	20	
Thermal properties			
Vicat softening temperature ⁴⁾			ASTM D 1525
at 10 N (VST/A)	°C	145	
at 50 N (VST/B)	°C	86	

1) All measurements on injection molded samples.

2) Speed of testing: 50 mm/min

3) Speed of testing: 5 mm/min

4) Temperature rate: 120°C/h



SABIC® PP 4935

PP random for Automotive injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.