+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





SABIC® PP 513A

PP homopolymer for Fibre, filament and tape extrusion

Description:

SABIC® PP 513A is a fibre grade with an anti gas fading stabiliser package.

Application:

SABIC® PP 513A is suitable for extrusion of staple fibres used in geo-textile applications with an optimum balance of tenacity/elongation.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site http://www.SABIC-europe.com

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 (www.ul.com)

IMDS 7172624

Typical values Revision 20140109

i ypicai values				1/6/13/01/20 140 100
Properties		Unit (Si)	Values	Test methods
Polymer properties				
Melt flow rate (MFR)				ASTM D 1238
at 230 °C and 2.16 kg		g/10 min	6.0	
Density		kg/m³	905	ASTM D 792
Molecular Weight Distribution		-	Broad	-
Isotacticity		-	Medium	-
Formulation				
Gas fading stabilized		_	Yes	-
Mechanical properties				
Tensile test				ASTM D 638
stress at yield	1)	MPa	37	
strain at yield	1)	%	8	
secant modulus at 1% elongation	2)	MPa	1800	

¹⁾ Speed of testing: 50 mm/min

²⁾ Speed of testing: 1 mm/min

+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





SABIC® PP 513A

PP homopolymer for Fibre, filament and tape extrusion

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.