#### +135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





# **SABIC® PP 527K**

## PP homopolymer for Thermoforming

### **Description:**

SABIC® PP 527K is a leading grade typically used for products in thermoforming. Tailoring of the polymer architecture combined with effective nucleation resulted in a good balance of very high stiffness combined with excellent transparency. Its high crystallisation temperature is ideally suited for further line speed improvements. Moreover it is formulated with a combined processing and antistatic additive package.

### **Application:**

SABIC® PP 527K is typically used in packaging for Fruit, Vegetables, Meat, Fish, Poultry and Ambient Food packaging.

#### Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site http://www.sabic.com/europe/en/products-services/

This product is not intended for and must not be used in any pharmaceutical/medical applications.

IMDS 7172624

Typical values			Revision 20150303		
Properties		Unit (Si)	Values	Test methods	
Polymer properties					
Melt flow rate (MFR) at 230 °C and 2.16 kg		g/10 min	3.0	ASTM D 1238	
Density		kg/m <sup>3</sup>	905	ASTM D 792	
Molecular Weight Distribution		-	Broad High	-	
Formulation			- ingli		
Anti static agent Nucleating agent		-	Yes Yes	-	
Mechanical properties					
Tensile test stress at yield strain at yield	1) 1)	MPa %	40 6	ASTM D 638	
secant modulus at 1% elongation Izod impact notched at 23 °C	2)	MPa J/m	2300 30	ASTM D 256A	
Thermal properties					
Heat deflection temperature at 1.80 MPa (HDT/A) at 0.45 MPa (HDT/B)		°C °C	70 120	ASTM D 648	
vicat softening temperature at 10 N (VST/A) at 50 N (VST/B)	3)	°C °C	155	ASTM D 1525	

1) Speed of testing: 50 mm/min

Speed of testing: 1 mm/min
Temperature rate: 120°C/h

#### +135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





# SABIC® PP 527K

## PP homopolymer for Thermoforming

#### Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

#### Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

**Disclaimer.** The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.