



## SABIC® PP 571P

### PP homopolymer for Thermoforming

#### Description:

SABIC® PP 571P is a higher flow material typically used in extrusion applications like sheet and thermoforming. This grade combines higher mfi and high stiffness.

#### Application:

SABIC® PP 571P is typically used in off line thermoforming processes. The higher mfi is seen by our customers as advantages as they can run faster and have better wall thickness control of the sheet. These advances are then extrapolated to the forming step of the process. Other application that could be thought of are blister packaging where very thin packaging is required. The higher mfi makes it easier to run thinner sheet.

#### Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site  
<http://www.sabic.com/europe/en/products-services/>

This product is not intended for and must not be used in any pharmaceutical/medical applications.

This grade material is UL registered under File E111275 (www.ul.com) / IMDS 7172624

#### Typical values

Revision 20150303

Properties	Unit (Si)	Values	Test methods
<b>Polymer properties</b>			
<b>Melt flow rate (MFR)</b> at 230 °C and 2.16 kg	g/10 min	<b>5.7</b>	ASTM D 1238
<b>Density</b>	kg/m³	<b>905</b>	ASTM D 792
<b>Molecular Weight Distribution</b>	-	<b>Broad</b>	-
<b>Isotacticity</b>	-	<b>Medium</b>	-
<b>Formulation</b>			
<b>Anti static agent</b>	-	<b>No</b>	-
<b>Nucleating agent</b>	-	<b>No</b>	-
<b>Mechanical properties</b>			
<b>Tensile test</b>			ASTM D 638
stress at yield <sup>1)</sup>	MPa	<b>37</b>	
strain at yield <sup>1)</sup>	%	<b>8</b>	
secant modulus at 1% elongation <sup>2)</sup>	MPa	<b>1800</b>	
<b>Izod impact notched</b> at 23 °C	J/m	<b>25</b>	ASTM D 256A
<b>Thermal properties</b>			
<b>Heat deflection temperature</b> at 1.80 MPa (HDT/A) at 0.45 MPa (HDT/B)	°C °C	<b>60</b> <b>90</b>	ASTM D 648
<b>Vicat softening temperature</b> at 10 N (VST/A) at 50 N (VST/B)	°C °C	<b>154</b> <b>95</b>	ASTM D 1525

1) Speed of testing: 50 mm/min

2) Speed of testing: 1 mm/min

3) Temperature rate: 120°C/h



## SABIC® PP 571P

### PP homopolymer for Thermoforming

**Quality:**

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

**Storage and handling:**

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

**Disclaimer.** The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.