+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





SABIC® PP 576S

PP homopolymer for Injection moulding

Description:

SABIC® PP 576S is a PP homopolymer grade that has good flow properties, excellent demoulding properties and a narrow molecular weight distribution. Products made from SABIC® PP 576S typically have low warpage, high stiffness in combination with moderate impact strength at room temperature and a high gloss.

Application:

SABIC® PP 576S is typically used in caps & closures and thin wall packaging both in food and non-food segments, and appliances.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site http://www.SABIC-europe.com

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 (www.ul.com)

IMDS 7172624

Typical values Revision 20140109

Properties		Unit (Si)	Values	Test methods
Polymer properties				
Melt flow rate (MFR) at 230 °C and 2.16 kg Density		g/10 min kg/m³	19 905	ASTM D 1238 ASTM D 792
Formulation				
Anti static agent Nucleating agent		-	Yes No	-
Mechanical properties				
Tensile test stress at yield strain at yield secant modulus at 1% elongation lzod impact notched at 23 °C Rockwell hardness R-scale	1) 1) 2)	MPa % MPa J/m	37 9 1850 25	ASTM D 638 ASTM D 256A ASTM D 785
Thermal properties				
Heat deflection temperature at 1.80 MPa (HDT/A) at 0.45 MPa (HDT/B) Vicat softening temperature at 10 N (VST/A) at 50 N (VST/B)	3)	့ ့ ့	65 95 152 94	ASTM D 648 ASTM D 1525

Speed of testing: 50 mm/min

Speed of testing: 5 mm/min
 Speed of testing: 1 mm/min
 Temperature rate: 120°C/h

+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





SABIC® PP 576S

PP homopolymer for Injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.