

SABIC® PP 620P

PP random copolymer for Sheet extrusion

Description:

SABIC® PP 620P is a general purpose random PP grade primarily produced for extrusion applications. Due to its basic design, it can be used in a wide range of applications. With the well balance mechanical properties and easy extrusion behaviour, it is highly useful in a wide range of applications.

Applications:

Typical applications are: extrusion blow moulding, sheet extrusion and other extrusion applications

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site
<http://www.SABIC-europe.com>

Typical values


Revision 20140109

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	g/10 min	1.7	ASTM D 1238
Density	kg/m³	905	ASTM D 792
Molecular Weight Distribution	-	Broad	-
Isotacticity	-	Medium	-
Mechanical properties			
Tensile test			ASTM D 638
stress at yield ¹⁾	MPa	26	
strain at yield ¹⁾	%	13	
secant modulus at 1% elongation ²⁾	MPa	950	
Izod impact notched at 23 °C	J/m	200	ASTM D 256A
Rockwell hardness R-scale	-	92	ASTM D 785
Thermal properties			
Vicat softening temperature ³⁾			ASTM D 1525
at 10 N (VST/A)	°C	128	
at 50 N (VST/B)	°C	63	

1) Speed of testing: 50 mm/min

2) Speed of testing: 1 mm/min

3) Temperature rate: 120°C/h



SABIC® PP 620P

PP random copolymer for Sheet extrusion

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.