



SABIC® PP 622L

PP random copolymer for Cast film

Description: SABIC®PP 622L is a polypropylene random copolymer resin specifically designed for cast film applications. Products produced out of SABIC®PP 622L have a high clarity, excellent sealing performance and high puncture resistance. The molecular structure of this grade is tailored for high performance processing. SABIC®PP 622L contains anti-block and slip agent for low coefficient of friction. A grade without anti-block and slip agent is available as SABIC®PP 621P.

Applications:

SABIC PP 622L is typically used in applications like food packaging, lamination film, stationary film, textile packaging, flower packaging, and hygiene packaging.

Health, Safety and Food Contact regulations: SABIC®PP 622L is compliant to food contact regulations. Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

IMDS 80775790

Typical values

Revision 20140109

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 5 kg	g/10 min	8.0	ASTM D 1238
Density	kg/m³	905	ASTM D 792
Molecular Weight Distribution	-	Narrow	-
Formulation			
Anti block agent	-	Yes	-
Slip agent	-	Yes	-
Mechanical properties			
Tensile test			ASTM D 638
stress at yield ¹⁾	MPa	26	
strain at yield ¹⁾	%	14	
secant modulus at 1% elongation ²⁾	MPa	900	
Optical properties			
Haze ³⁾	%	< 2	ASTM D 1003
Thermal properties			
Vicat softening temperature ⁴⁾			ASTM D 1525
at 10 N (VST/A)	°C	128	
at 50 N (VST/B)	°C	63	

1) Speed of testing: 50 mm/min

2) Speed of testing: 5 mm/min

3) Determined at film of 25 µm

4) Temperature rate: 120°C/h



SABIC® PP 622L

PP random copolymer for Cast film

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.