+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





## **SABIC® PP 95610**

PP super high impact for Automotive injection moulding

### **Description:**

SABIC® PP 95610 is a reactor-elastomer-modified material which offers an excellent cold impact resistance. It is a highly attractive alternative to non-filled compounds and is commonly used for car bumpers.

SABIC® PP 95610 is a designated automotive grade.

IMDS ID: 80775790

**Typical values** Revision 20140109 **Properties** Unit (Si) Values Test methods Polymer properties Melt flow rate (MFR) **ASTM D 1238** at 230 °C and 2.16 kg g/10 min 6 Density kg/m³ 900 **ASTM D 792** 1) Mould shrinkage SABIC method 24 hours after injection moulding % 1.5 Formulation Anti static agent No **Nucleating agent** No **Mechanical properties** ASTM D 638 Tensile test 2) stress at yield MPa 18 2) strain at yield 3) secant modulus at 1% elongation MPa 950 Izod impact notched ASTM D 256A at 23 °C J/m No Break at 0 °C J/m No Break at -20 °C No Break J/m Thermal properties Vicat softening temperature **ASTM D 1525** at 10 N (VST/A) °C 125 at 50 N (VST/B) °C 49

<sup>1)</sup> All measurements on injection molded samples.

Speed of testing: 50 mm/min

Speed of testing: 5 mm/min Temperature rate: 120°C/h

+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





# **SABIC® PP 95610**

## PP super high impact for Automotive injection moulding

#### Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

### Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

**Disclaimer.** The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.