



SABIC® PP CX02-82

PP high crystallinity for Automotive injection moulding

Description:

SABIC® PP CX02-82 is an emission optimised high crystalline copolymer. It offers high stiffness, in perfect balance with high thermal dimensional stability, impact resistance and flow. This material has excellent aesthetic properties as well and is typically used for automotive interior applications. It is the obvious alternative to conventional talc-filled copolymers, offering considerable weight saving advantage.

SABIC® PP CX02-82 is a designated automotive grade.

IMDS ID: 80775790

Typical values

Revision 20140109

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	g/10 min	15	ASTM D 1238
Density	kg/m ³	905	ASTM D 792 SABIC method
Mould shrinkage 24 hours after injection moulding	%	1.6	VDA 277
Emission	µg C/g	<50	
Formulation			
UV stabilized	-	Yes	-
Anti static agent	-	No	-
Nucleating agent	-	Yes	-
Mechanical properties			
Tensile test			ASTM D 638
stress at yield	MPa	26	
strain at yield	%	4	
secant modulus at 1% elongation	MPa	1600	
Izod impact notched			ASTM D 256A
at 23 °C	J/m	100	
at 0 °C	J/m	75	
at -20 °C	J/m	70	
Thermal properties			
Vicat softening temperature			ASTM D 1525
at 10 N (VST/A)	°C	151	
at 50 N (VST/B)	°C	80	

1) All measurements on injection molded samples.

2) Speed of testing: 50 mm/min

3) Speed of testing: 5 mm/min

4) Temperature rate: 120°C/h



SABIC® PP CX02-82

PP high crystallinity for Automotive injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.