

ExxonMobil™ LLDPE LL 1002AY

Linear Low Density Polyethylene Resin

产品说明

LL 1002AY is a butene LLDPE designed for the blown film process, offering high gloss and excellent draw down. Films made from LL1002AY have very good tensile and toughness properties. TnPP is not intentionally added to LL 1002AY.

总览

供货地区 ¹	- 拉丁美洲 - 欧洲 - 亚太地区
添加剂	LL 1002AY: 开口: 否; 爽滑: 否; 加工助剂: 否; 热稳定剂: 是
应用	- 包装膜 - 成卷农产品包装袋 - 成形、填充和封口包装 - 成衣包装膜 - 吹膜 - 地面覆盖薄膜 - 多层包装膜 - 复合膜 - 个人护理 - 工业包装 - 购物袋 - 规格空罐内涂料 - 垃圾桶衬层 - 冷冻膜 - 流延膜 - 内衬袋 - 农用薄膜 - 食品包装 - 通用包装 - 箱中袋
修订日期	01/01/2019

物理性能	典型数值 (英制)	典型数值 (公制)	测试方法
密度	0.918 g/cm ³	0.918 g/cm ³	ASTM D1505
熔融指数 (190° C/2.16 kg)	2.0 g/10 min	2.0 g/10 min	ASTM D1238
熔融峰值温度	250 ° F	121 ° C	ExxonMobil Method

薄膜	典型数值 (英制)	典型数值 (公制)	测试方法
MD 屈服拉伸强度	1400 psi	9.4 MPa	ASTM D882
TD 屈服拉伸强度	1300 psi	8.9 MPa	ASTM D882
MD 断裂拉伸强度	7100 psi	49 MPa	ASTM D882
TD 断裂拉伸强度	4200 psi	29 MPa	ASTM D882
MD 断裂伸长率	590 %	590 %	ASTM D882
TD 断裂伸长率	800 %	800 %	ASTM D882
割线模量 TD - 1% 正割	32000 psi	220 MPa	ASTM D882
落锤冲击	70 g	70 g	ASTM D1709A
埃尔曼多夫抗撕强度 MD	90 g	90 g	ASTM D1922
埃尔曼多夫抗撕强度 TD	400 g	400 g	ASTM D1922

光学性能	典型数值 (英制)	典型数值 (公制)	测试方法
光泽度 (45°)	76	76	ASTM D2457
雾度	4.4 %	4.4 %	ASTM D1003

法律声明

本产品不宜在医疗应用中使用，亦不应在任何此类应用中使用

加工说明

The test specimen was prepared and tested at our European Technology Center using a 25.4 µm (1.0 mil) thick film (screw diameter = 75 mm, die gap = 2.5 mm, BUR = 2.5 and temperature setting of 200° C). Optical film properties have been measured on a 25.4 µm thick film with addition of 10% LDPE at the same conditions.

备注

典型数值：此等典型数值不应被解释为规格。

¹ 在所标识的可供应区域的一个或多个国家/地区中可能无法供应此产品。请联系您的销售代表以获取完整的可供应国家/地区列表

ExxonMobil™ LLDPE LL 1002AY
Linear Low Density Polyethylene Resin

标准免责声明中文译文 www.exxonmobilchemical.com/ContactUs

©2019 埃克森美孚。埃克森美孚（ExxonMobil），埃克森美孚的徽标（ExxonMobil logo）及连接的“X”设计和在本文件中使用的所有其他产品或服务名称，除非另有标明，否则均为埃克森美孚的商标。未经埃克森美孚的事先书面授权，不得分发、展示、复印或改变本文件。使用者可在埃克森美孚授权的范围内，分发、展示和/或复印本文件，但必须毫无改动并保持其完整性，包括所有的页眉、脚注、免责声明及其它信息。使用者不可将本文件全文或部份复制到任何网站。埃克森美孚不保证典型（或其它）数值。本文件包含的所有数据是基于代表性样品的分析，而不是实际运送的产品。本文件所含信息仅是所指明的产品或材料未与任何其它产品或材料结合使用时的相关信息。我们的信息基于收集之日被认为可靠的数据，但是，我们并不明示或暗示地陈述、担保或以其它方式保证此信息或所描述产品、材料或工艺的适销性、适宜于某一特定用途、不侵犯专利权、适用性、准确性、可靠性或完整性。使用者对在其感兴趣的领域使用该材料、产品或工艺所做的一切决定负全部责任。我们明确声明将不对由于任何人使用或依赖本文件所含任何信息而导致的或与此相关的直接或间接遭受或者产生的任何损失、损害或伤害承担责任。本文件不应视作我们对任何非埃克森美孚产品或工艺的认可，并且我们明确否认任何相反的含意。“我们”、“我们的”、“埃克森美孚化工”或“埃克森美孚”等词语均为方便而使用，可包括埃克森美孚化工公司、埃克森美孚公司，或由它们直接或间接控制的任何关联公司中的一家或者多家。

exxonmobilchemical.com