



SABIC® PP PHC26

PP block copolymer for Injection moulding

Description: This grade combines very high impact resistance, also at low temperatures, with high stiffness and offers good flow properties. Due to its narrow molecular weight distribution, the very low tendency to warp and the excellent surface quality, SABIC® PP PHC26 is typically used in injection moulding of suitcase shells, crates & boxes and automotive parts.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site
<http://www.SABIC-europe.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

IMDS 80775790

Typical values

Revision 20140109

Revision 2014010

Typical values	Properties	Unit (Si)	Values	Test methods
	Polymer properties			
	Melt flow rate (MFR) at 230 °C and 2.16 kg	g/10 min	8.0	ASTM D 1238
	Density	kg/m³	905	ASTM D 792
	Formulation			
	UV stabilized	-	No	-
	Anti static agent	-	No	-
	Nucleating agent	-	Yes	-
	Mechanical properties			
	Tensile test			ASTM D 638
	stress at yield1)	MPa	22	ASTM D 256A
	strain at yield1)	%	6	
	secant modulus at 1% elongation2)	MPa	1300	
	Izod impact notched			ASTM D 785
	at 23 °C	J/m	No Break	
	at 0 °C	J/m	200	
	at -20 °C	J/m	110	
	Rockwell hardness			
	R-scale	-	85	
	Thermal properties			
	Heat deflection temperature			ASTM D 648
	at 1.80 MPa (HDT/A)	°C	55	ASTM D 1525
	at 0.45 MPa (HDT/B)	°C	90	
	Vicat softening temperature3)			
	at 10 N (VST/A)	°C	147	
	at 50 N (VST/B)	°C	68	

1) Speed of testing: 50 mm/min

2) Speed of testing: 5 mm/min

3) Temperature rate: 120°C/h



SABIC® PP PHC26

PP block copolymer for Injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.