



# **SABIC® PP RA12MN40**

## PP random copolymer for Injection moulding

#### **Description:**

This random copolymer is medium ethylene modified, clarified and anti-static. It is specially developed for injection moulding applications. Special characteristics are high stiffness, good transparancy and high gloss. Typical applications are in housewares and thin walled packaging.

#### Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site http://www.SABIC-europe.com

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 (www.ul.com) / IMDS 80775790

Typical values				Revision 20140109
Properties		Unit (Si)	Values	Test methods
Polymer properties				
Melt flow rate (MFR)				ASTM D 1238
at 230 °C and 2.16 kg		g/10 min	40	
Density		kg/m³	905	ASTM D 792
Formulation				
Clarified		-	Yes	-
Anti static agent		-	Yes	-
Mechanical properties				
Tensile test				ASTM D 638
stress at yield	1)	MPa	27	
strain at yield	1)	%	13	
secant modulus at 1% elongation	2)	MPa	1100	
Izod impact notched				ASTM D 256A
at 23 °C		J/m	50	
at 0 °C		J/m	30	
Rockwell hardness				ASTM D 785
R-scale		-	95	
Thermal properties				
Heat deflection temperature				ASTM D 648
at 1.80 MPa (HDT/A)		°C	55	
at 0.45 MPa (HDT/B)	3)	°C	80	
Vicat softening temperature	0)	°C	126	ASTM D 1525
at 10 N (VST/A)		0°C	68	
at 50 N (VST/B)			00	

1) Speed of testing: 50 mm/min

Speed of testing: 0 min.....
Speed of testing: 1 mm/min
Temperature rate: 120°C/h

. .

#### +135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





## SABIC® PP RA12MN40

### PP random copolymer for Injection moulding

#### Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

#### Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

**Disclaimer.** The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.