



SABIC[®] PP 412MN40

PP IMPACT COPOLYMER

DESCRIPTION

SABIC[®] PP 412MN40 is a multi-purpose grade with good flow properties, combining stiffness and good balance in impact strength. The material has a very low tendency for warpage and is typically used for the production of thin wall packaging articles. Cycle times can be very short. It is formulated with a combined processing and antistatic additive package. This grade is widely applied in thin wall technical injection moulded articles and thin-walled containers, in particular where dimensional stability is important.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 (www.ul.com) / IMDS 80775790

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	37	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
FORMULATION			
Anti static agent	☒	-	-
Nucleating agent	☐	-	-
MECHANICAL PROPERTIES			
Tensile test			
tensile modulus ⁽¹⁾	1300	MPa	ISO 527-2 1A
stress at yield	25	MPa	ISO 527-2 1A
strain at yield ⁽²⁾	5	%	ISO 527-2 1A
Izod impact notched			
at 0 °C	6.5	kJ/m ²	ISO 180/1A
at -20 °C	5	kJ/m ²	ISO 180/1A
at 23 °C	8	kJ/m ²	ISO 180/1A
Charpy Impact Strength Notched			
at -20 °C	5	kJ/m ²	ISO 179/1eA
at 23 °C	11	kJ/m ²	ISO 179/1eA
at 0 °C	7	kJ/m ²	ISO 179/1eA
Hardness Shore D	63	-	ISO 868
THERMAL PROPERTIES			
Heat deflection temperature ⁽³⁾			
at 0.45 MPa (HDT/B)	85	°C	ISO 75
at 1.80 MPa (HDT/A)	55	°C	ISO 75
Vicat Softening Temperature ⁽⁴⁾			
at 10 N (VST/A)	150	°C	ISO 306
at 50 N (VST/B)	75	°C	ISO 306



- (1) Speed of testing: 1 mm/min
- (2) Speed of testing: 50 mm/min
- (3) Flat wise (testbar 80*10*4mm)
- (4) Temperature rate: 120°C/h

QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.