



SABIC[®] PP 521P

POLYPROPYLENE HOMOPOLYMER

DESCRIPTION

SABIC[®] PP 521P is particularly designed for (biaxially) oriented PP film extrusion with a very specific molecular structure providing the ultimate properties required for the stretching process.

TYPICAL APPLICATIONS

SABIC[®] PP 521P is typically used in mono layer or coextruded (B)OPP film. SABIC[®]PP 521P is known for its excellent n=metallisation behaviour. It can also be used as base material for plain film for stationary, dry food bags, synthetic paper and heat sealable packaging films.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	3	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
Molecular Weight Distribution	Broad	-	-
Isotacticity	Medium	-	-
FORMULATION			
Anti block agent	<input type="checkbox"/>	-	-
Slip agent	<input type="checkbox"/>	-	-
Anti static agent	<input type="checkbox"/>	-	-
Nucleating agent	<input type="checkbox"/>	-	-
Gas fading stabilized	<input type="checkbox"/>	-	SABIC method
MECHANICAL PROPERTIES			
Tensile test			
strain at break	600	%	ISO 527
stress at break	34	MPa	ISO 527
stress at yield ⁽¹⁾	36	MPa	ISO 527-2 1A
tensile modulus ⁽²⁾	1550	MPa	ISO 527-2 1A
strain at yield	10	%	ISO 527-2 1A
Flexural test			
Flexural modulus	1500	MPa	ASTM D790
THERMAL PROPERTIES			
Vicat Softening Temperature ⁽³⁾			
at 10 N (VST/A)	155	°C	ISO 306/A
at 50 N (VST/B)	88	°C	ISO 306

(1) Speed of testing: 50 mm/min

(2) Speed of testing: 1 mm/min

(3) Temperature rate: 120°C/h



PROCESSING CONDITIONS

Typical processing conditions for 521P are:

Average extrusion temperature range may be kept at 245 - 255°C.

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>. For additional specific information please contact SABIC local representative.

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/medical applications.

IMDS 7172624

QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.