



SABIC® PP 528K

POLYPROPYLENE HOMOPOLYMER FOR THERMOFORMING

DESCRIPTION

SABIC® PP 528K is formulated with an advanced agent and is specially developed for in-line and off-line thermoforming applications.

PP 528K encompasses the following features: high stiffness, good clarity, very good dimensional stability, easy process ability and faster cycling.

TYPICAL APPLICATIONS

SABIC® PP 528K is used for the production of containers mainly for food and health drink products such as cups, trays and lids.

TYPICAL PROPERTY VALUES

Revision 20190328

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230°C and 2.16kg	3	g/10 min	ASTM D1238
Density			
at 23°C	905	kg/m³	ASTM D792
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile Properties			
Strength @ Yield	37	MPa	ASTM D 638
Elongation @ Yield	10	%	ASTM D 638
Flexural Modulus (1% Secant)	1700	MPa	ASTM D790 A
Izod Impact Strength			
notched, at 23°C	35	J/m	ASTM D256
Rockwell Hardness, R-Scale	102	-	ASTM D785
THERMAL PROPERTIES			
Vicat Softening Temperature	150	°C	ASTM D1525
Heat deflection temperature			
at 455kPa	112	°C	ASTM D648

(1) Based on injection molded specimens

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

SABIC® PP 528K is suitable for food contact application. Detailed information is provided in relevant documents / certificates and for additional specific information please contact SABIC local representative.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical / medical applications.

STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.