



SABIC[®] PP 576P

PP HOMOPOLYMER

DESCRIPTION

SABIC[®] PP 576P is a PP homopolymer grade that has good flow properties and a narrow molecular weight distribution. Products made from SABIC[®] PP 576P typically have low warpage and a high gloss, high stiffness in combination with moderate impact strength at room temperature.

Application:

SABIC[®] PP 576P is typically used in caps & closures and thin wall packaging both in food and non-food segments.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site
<http://www.SABIC.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 (www.ul.com)
IMDS 7172624

TYPICAL PROPERTY VALUES

Revision 20181206

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	19	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
FORMULATION			
Anti static agent	□	-	-
Nucleating agent	□	-	-
MECHANICAL PROPERTIES			
Tensile test			
strain at yield ⁽¹⁾	9	%	ISO 527-2 1A
tensile modulus ⁽²⁾	1800	MPa	ISO 527-2 1A
stress at yield	37	MPa	ISO 527-2 1A
Izod impact notched			
at 23 °C	3.0	kJ/m ²	ISO 180/1A
Charpy Impact Strength Notched			
at 23 °C	4.0	kJ/m ²	ISO 179/1eA
Hardness Shore D	71	-	ISO 868
THERMAL PROPERTIES			
Heat deflection temperature ⁽³⁾			
at 1.80 MPa (HDT/A)	60	°C	ISO 75
at 0.45 MPa (HDT/B)	90	°C	ISO 75
Vicat Softening Temperature ⁽⁴⁾			
at 50 N (VST/B)	94	°C	ISO 306
at 10 N (VST/A)	152	°C	ISO 306



- (1) Speed of testing: 50 mm/min
- (2) Speed of testing: 1 mm/min
- (3) Flat wise (testbar 80*10*4mm)
- (4) Temperature rate: 120°C/h

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.