



# SABIC<sup>®</sup> PP 576S

## PP HOMOPOLYMER

### DESCRIPTION

SABIC<sup>®</sup> PP 576S is a PP homopolymer grade that has good flow properties, very good demoulding properties and a narrow molecular weight distribution. Products made from SABIC<sup>®</sup> PP 576S typically have low warpage and a high gloss, high stiffness in combination with moderate impact strength at room temperature.

Application: SABIC<sup>®</sup> PP 576S is typically used in caps & closures and thin wall packaging both in food and non-food segments, and appliances.

Health, Safety and Food Contact regulations: Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications. This grade material is UL registered under File E1 11275 ([www.ul.com](http://www.ul.com)) IMDS 7172624

### TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate</b>			
at 230 °C and 2.16 kg	19	dg/min	ISO 1133
<b>Density</b>	905	kg/m <sup>3</sup>	ASTM D1505
<b>FORMULATION</b>			
<b>Anti static agent</b>	<input checked="" type="checkbox"/>	-	-
<b>Nucleating agent</b>	<input type="checkbox"/>	-	-
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
tensile modulus <sup>(1)</sup>	1800	MPa	ISO 527-2 1A
strain at yield <sup>(2)</sup>	9	%	ISO 527-2 1A
stress at yield	37	MPa	ISO 527-2 1A
<b>Izod impact notched</b>			
at 23 °C	3.0	kJ/m <sup>2</sup>	ISO 180/1A
<b>Charpy Impact Strength Notched</b>			
at 23 °C	4.0	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Hardness Shore D</b>	71	-	ISO 868
<b>THERMAL PROPERTIES</b>			
<b>Heat deflection temperature <sup>(3)</sup></b>			
at 0.45 MPa (HDT/B)	90	°C	ISO 75
at 1.80 MPa (HDT/A)	60	°C	ISO 75
<b>Vicat Softening Temperature <sup>(4)</sup></b>			
at 50 N (VST/B)	94	°C	ISO 306
at 10 N (VST/A)	152	°C	ISO 306

(1) Speed of testing: 1 mm/min

(2) Speed of testing: 50 mm/min

(3) Flat wise ( testbar 80\*10\*4mm)

(4) Temperature rate: 120°C/h



## QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.