



SABIC[®] PP 57MNK10

POLYPROPYLENE IMPACT COPOLYMER FOR INJECTION MOLDING

DESCRIPTION

SABIC[®] PP 57MNK10 is a controlled rheology PP grade and specially developed for producing injection molded articles. This grade has excellent impact resistance (even at low temperature) and balanced stiffness.

TYPICAL APPLICATIONS

SABIC[®] PP 57MNK10 can be used for furniture, housewares, pails and containers, toys, crates and boxes.

TYPICAL PROPERTY VALUES

Revision 20190327

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES ⁽¹⁾			
Melt Flow Rate			
at 230°C and 2.16kg	12	g/10 min	ASTM D1238
Density			
at 23°C	905	kg/m ³	ASTM D792
MECHANICAL PROPERTIES			
Tensile Properties			
Strength @ Yield	24	MPa	ASTM D 638
Elongation @ Yield	4	%	ASTM D 638
Flexural Modulus (1% Secant)	1150	MPa	ASTM D790 A
Izod Impact Strength			
notched, at 23°C	115	J/m	ASTM D256
notched, at -20°C	63	J/m	ASTM D256
Rockwell Hardness, R-Scale ⁽¹⁾	80	-	ASTM D785
THERMAL PROPERTIES			
Vicat Softening Temperature	148	°C	ASTM D1525
Heat deflection temperature			
at 455kPa	90	°C	ASTM D648

(1) Typical values, not to be construed as specific limits

PROCESSING CONDITIONS

Typical processing conditions for 57MNK10 are:

Barrel temperature range: 200 - 250°C.

Mold shrinkage: 1.2 - 2.0% depending on wall thickness and processing conditions.

Mold temperature: normally 15 - 40°C, up to 65°C for thick parts.

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>. For additional specific information please contact SABIC local representative.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical / medical applications.



STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.