



# SABIC® PP 642NH-66408

POLYPROPYLENE RANDOM CO-POLYMER FOR PIPE

## DESCRIPTION

SABIC® PP 642NH-66408 is a high molecular weight, low melt flow rate polypropylene random copolymer (PP-R) green coloured and specially designed for transport of hot and cold drinking water. This grade is highly heat stabilized and specially formulated for extraction resistance with improved throughput & gloss. SABIC® PP 642NH-66408 is pre-color compounded version of SABIC® PP 651H PPR resin (Exova – MRS classification 8 MPa). SABIC® PP 642NH-66408 is a designated pipe grade.

## TYPICAL APPLICATIONS

SABIC® PP 642NH-66408 is a designated pipe grade.

## TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
<b>Flexural Modulus</b> <sup>(1)</sup>	1040	MPa	ISO 178
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate</b>			
at 230 °C and 2.16 kg	0.3	g/10 min	ISO 1133
<b>Density</b>	900	kg/m³	ASTM D1505
<b>Filler content</b> <sup>(2)</sup>	0.5	%	SABIC method
<b>Mould shrinkage</b>			
24 hours after injection moulding <sup>(2)</sup>	2.0	%	SABIC method
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
Tensile modulus	1000	MPa	ISO 527/1A
tensile strength	28	MPa	ISO 527/1A
stress at break	18	MPa	ISO 527/1A
strain at break	70	MPa	ISO 527/1A
<b>Izod impact notched</b>			
at 23 °C <sup>(1)</sup>	26	kJ/m²	ISO 180/1A
at 0 °C	3.5	kJ/m²	ISO 180/1A
at -20 °C	2.5	kJ/m²	ISO 180/1A
<b>THERMAL PROPERTIES</b>			
<b>Heat deflection temperature</b>			
HDT A (at 1.8 MPa)	49	°C	ISO 75
HDT B (at 0.45 MPa)	84	°C	ISO 75
<b>Coeff. of linear thermal expansion</b>			
CLTE -30 °C to 80 °C	126	µm/mK	ASTM D 696

(1) Injection molded sample ISO527-1A.

(2) Injection molded plaque 65x65x3.2 mm



## HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>. For additional specific information please contact SABIC local representative.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.