



CYCOLACTM RESIN DL100LG

REGION AMERICAS

DESCRIPTION

CYCOLAC DL100LG is a low gloss, high heat, high impact ABS/PC blend with low emission

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	51	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	38	MPa	ASTM D 638
Tensile Stress, yld, Type I, 5 mm/min	47	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	40	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	12	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	85	%	ASTM D 638
Tensile Modulus, 50 mm/min	2240	MPa	ASTM D 638
Tensile Stress, yield, 5 mm/min	47	MPa	ISO 527
Tensile Stress, break, 5 mm/min	36	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	51	MPa	ISO 527
Tensile Stress, break, 50 mm/min	39	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	50	%	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	12	%	ISO 527
Tensile Modulus, 1 mm/min	2200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	74	MPa	ISO 178
Flexural Modulus, 2 mm/min	2200	MPa	ISO 178
Hardness, H358/30	80	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched, 23°C	380	J/m	ASTM D 256
Izod Impact, notched, -30°C	115	J/m	ASTM D 256
Izod Impact, notched 80*10*3 +23°C	45	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	19	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 +23°C	28	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	11	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	22	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	11	kJ/m ²	ISO 179/1eA
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	85	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.2E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.3E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate A/50	118	°C	ISO 306

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate A/ 120	120	°C	ISO 306
Vicat Softening Temp, Rate B/50	105	°C	ISO 306
Vicat Softening Temp, Rate B/ 120	107	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	103	°C	ISO 75 /Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	84	°C	ISO 75 /Af
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 220°C/ 10.0 kgf	10	g/ 10 min	ASTM D 1238
Density	1.08	g/cm³	ISO 1183
Melt Volume Rate, MVR at 220°C/ 10.0 kg	10	cm³/ 10 min	ISO 1133
Melt Volume Rate, MVR at 260°C/5.0 kg	12	cm³/ 10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	90 – 100	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	250 – 280	°C	
Nozzle Temperature	245 – 275	°C	
Front - Zone 3 Temperature	250 – 280	°C	
Middle - Zone 2 Temperature	250 – 280	°C	
Rear - Zone 1 Temperature	230 – 260	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	40 – 80	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.