

GELOYTM RESIN XTPMFR10

REGION AMERICAS

DESCRIPTION

PC/ASA, chlorine and bromine free.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	65	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	47	MPa	ASTM D 638
Tensile Stress, yld, Type I, 5 mm/min	60	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	49	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	31	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	58	%	ASTM D 638
Tensile Modulus, 50 mm/min	2680	MPa	ASTM D 638
Tensile Stress, yield, 5 mm/min	61	MPa	ISO 527
Tensile Stress, break, 5 mm/min	46	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	66	MPa	ISO 527
Tensile Stress, break, 50 mm/min	47	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	50	%	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	21	%	ISO 527
Tensile Modulus, 1 mm/min	2680	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	97	MPa	ISO 178
Flexural Modulus, 2 mm/min	2720	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	330	J/m	ASTM D 256
Izod Impact, notched, -30°C	90	J/m	ASTM D 256
Multiaxial Impact	85	J	ISO 6603
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	12	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	13	kJ/m ²	ISO 179/1eA
THERMAL			
CTE, -40°C to 40°C, flow	6.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	96	°C	ISO 306
Vicat Softening Temp, Rate B/120	98	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	90	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	81	°C	ISO 75/Af

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
PHYSICAL			
Density	1.18	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 260°C/2.16 kg	30	cm ³ /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	105	Pa-s	ISO 11443
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating	1	mm	UL 94 by SABIC-IP
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	230 – 270	°C	
Nozzle Temperature	220 – 260	°C	
Front - Zone 3 Temperature	230 – 270	°C	
Middle - Zone 2 Temperature	220 – 260	°C	
Rear - Zone 1 Temperature	200 – 230	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	50 – 70	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

