

GELOYTM RESIN XTWM206

REGION AMERICAS

DESCRIPTION

ASA, Xtreme weatherability, high heat.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	46	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	37	MPa	ASTM D 638
Tensile Stress, yld, Type I, 5 mm/min	43	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	36	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	2.7	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	26	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.5	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	27	%	ASTM D 638
Tensile Modulus, 50 mm/min	2400	MPa	ASTM D 638
Tensile Modulus, 5 mm/min	2360	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	74	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2450	MPa	ASTM D 790
Hardness, Rockwell R	100	-	ASTM D 785
Tensile Stress, yield, 50 mm/min	45	MPa	ISO 527
Tensile Stress, break, 50 mm/min	36	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	2.8	%	ISO 527
Tensile Strain, break, 50 mm/min	36	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	64	MPa	ISO 178
Flexural Modulus, 2 mm/min	2380	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	210	J/m	ASTM D 256
Izod Impact, notched, -30°C	35	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	36	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	3	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	3	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	11	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	98	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	97	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	84	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.4E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.4E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	8.3E-05	1/°C	ISO 11359-2

© 2019 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERSTM



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, xflow	9.4E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	Pass85	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	95	°C	ISO 306
Vicat Softening Temp, Rate B/120	99	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	98	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	84	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.09	-	ASTM D 792
Mold Shrinkage on Tensile Bar, flow	0.4 – 0.7	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.75	%	SABIC method
Melt Flow Rate, 220°C/10.0 kgf	8.8	g/10 min	ASTM D 1238
Melt Flow Rate, 260°C/5.0 kgf	7.1	g/10 min	ASTM D 1238
Melt Flow Rate, 280°C/3.8 kgf	7.2	g/10 min	ASTM D 1238
Density	1.09	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.5	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62
Melt Volume Rate, MVR at 260°C/5.0 kg	9	cm³/10 min	ISO 1133
OPTICAL			
Gloss, untextured, 60 degrees	93	-	ASTM D 523
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-486714	-	-
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
UV-light, water exposure/immersion	F1	-	UL 746C
INJECTION MOLDING			
Drying Temperature	85 – 90	°C	
Drying Time	4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	240 – 270	°C	
Nozzle Temperature	220 – 255	°C	
Front - Zone 3 Temperature	230 – 260	°C	
Middle - Zone 2 Temperature	220 – 255	°C	
Rear - Zone 1 Temperature	215 – 250	°C	
Mold Temperature	60 – 85	°C	
Back Pressure	0.3 – 1	MPa	
Screw Speed	30 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

