+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



SABIC® PPCOMPOUND G1120U

PP SHORT GLASS FIBER REINFORCED

DESCRIPTION

SABIC[®] PPcompound G1120U is a 20% short glass fiber reinforced and UV stabilized Polypropylene. The base material is a PP homopolymer optimized for good creep resistance. The glass fibres are hydrolytically stable and are chemically coupled to the PP matrix.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	3	dg/min	ISO 1133
Density ⁽¹⁾	1040	kg/m³	ISO 1183
Filler content	20	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	0.69	%	SABIC method
MECHANICAL PROPERTIES (1)			
Tensile test			
Tensile modulus	4500	MPa	ISO 527/1A
stress at break	80	MPa	ISO 527/1A
strain at break	3.7	%	ISO 527/1A
Flexural test			
Flexural modulus	4330	MPa	ISO 178/1A
Charpy Impact Strength Notched			
at 23 °C	11	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES (1)			
Heat deflection temperature			
at 1.80 MPa (HDT/A)	145	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	52	μm/mK	ISO 11359-2

⁽¹⁾ Injection molded sample ISO527-1A

QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO9001.

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

⁽²⁾ Injection molded plaque 65x65x3.2mm

+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.