

XENOVYTM RESIN 1103

REGION AMERICAS

DESCRIPTION

AUTOMOTIVE. Unreinforced, impact modified PBT+PC alloy. Excellent low temperature impact and chemical resistance. Range gray, black colors.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	51	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	50	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	150	%	ASTM D 638
Tensile Modulus, 50 mm/min	1890	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	77	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	1930	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	747	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	61	J	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	125	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	104	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	87	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.71E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	2.E-04	1/°C	ASTM E 831
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.8 – 1	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	13	g/10 min	ASTM D 1238
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-100149124	-	-
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	255 – 275	°C	
Nozzle Temperature	250 – 265	°C	
Front - Zone 3 Temperature	250 – 270	°C	
Middle - Zone 2 Temperature	245 – 265	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Mold Temperature	40 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Screw Speed	40 – 80	rpm	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

