

XENOVY™ RESIN 1731

REGION AMERICAS

DESCRIPTION

Impact/chemical resistant. UV-Stabilized. Excellent physical property retention in automotive exteriors and OVAD.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	61	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	56	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D 638
Tensile Modulus, 5 mm/min	2370	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	60	MPa	ISO 527
Tensile Stress, break, 50 mm/min	58	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	90	%	ISO 527
Tensile Modulus, 1 mm/min	2330	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	93	MPa	ISO 178
Flexural Modulus, 2 mm/min	2210	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	667	J/m	ASTM D 256
Izod Impact, notched, -30°C	106	J/m	ASTM D 256
Izod Impact, notched, 23°C, 6.4mm	160	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	61	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	61	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	59	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	16	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	65	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	125	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	93	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	115	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	107	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.75E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.57E-05	1/°C	ASTM E 831
CTE, -40°C to 95°C, flow	8.28E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.75E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.57E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	127	°C	ISO 306
Vicat Softening Temp, Rate B/120	130	°C	ISO 306

© 2019 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	99	°C	ISO 75/Af
Relative Temp Index, Elec	75	°C	UL 746B
Relative Temp Index, Mech w/impact	75	°C	UL 746B
Relative Temp Index, Mech w/o impact	75	°C	UL 746B
PHYSICAL			
Specific Gravity	1.22	-	ASTM D 792
Specific Volume	0.82	cm³/g	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.6 – 0.8	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	9.6	g/10 min	ASTM D 1238
Density	1.22	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.28	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Flow Rate, 250°C/5.0 kg	8	g/10 min	ISO 1133
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-220835	-	-
UL Recognized, 94HB Flame Class Rating	1.49	mm	UL 94
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 275	°C	
Nozzle Temperature	255 – 270	°C	
Front - Zone 3 Temperature	255 – 275	°C	
Middle - Zone 2 Temperature	250 – 270	°C	
Rear - Zone 1 Temperature	245 – 265	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

