

XENOVY™ RESIN 6620

REGION AMERICAS

DESCRIPTION

PBT+PC, Unreinforced, impact modified thermoplastic alloy. Outstanding impact at low temperature

TYPICAL PROPERTY VALUES

Revision 20190815

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	43	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	175	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	64	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	1720	MPa	ASTM D 790
Hardness, Rockwell R	108	-	ASTM D 785
IMPACT			
Izod Impact, unnotched, 23°C	1602	J/m	ASTM D 4812
Izod Impact, notched, 23°C	850	J/m	ASTM D 256
Izod Impact, notched, -30°C	667	J/m	ASTM D 256
Gardner, 23°C	54	J	ASTM D 3029
Modified Gardner, 23°C	54	J	ASTM D 3029
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	93	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	53	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	98	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	60	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.4E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.8E-05	1/°C	ASTM E 831
CTE, 60°C to 138°C, flow	1.03E-04	1/°C	ASTM E 831
Relative Temp Index, Elec	75	°C	UL 746B
Relative Temp Index, Mech w/impact	75	°C	UL 746B
Relative Temp Index, Mech w/o impact	75	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Specific Volume	0.83	cm³/g	ASTM D 792
Water Absorption, 24 hours	0.08	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	1.5 – 2.0	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	1.6 – 1.8	%	SABIC method
ELECTRICAL			
Volume Resistivity	5.5E+16	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	19	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	27.9	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	19	kV/mm	ASTM D 149
Relative Permittivity, 100 Hz	3.1	-	ASTM D 150

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Permittivity, 100 kHz	3	-	ASTM D 150
Relative Permittivity, 1 MHz	3	-	ASTM D 150
Dissipation Factor, 100 Hz	0.002	-	ASTM D 150
Dissipation Factor, 100 kHz	0.02	-	ASTM D 150
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-221088	-	-
UL Recognized, 94HB Flame Class Rating	1.47	mm	UL 94
INJECTION MOLDING			
Drying Temperature	105 – 115	°C	
Drying Time	2 – 4	hrs	
Drying Time (Cumulative)	6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	240 – 260	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	240 – 260	°C	
Middle - Zone 2 Temperature	230 – 250	°C	
Rear - Zone 1 Temperature	225 – 245	°C	
Mold Temperature	50 – 80	°C	
Back Pressure	0.2 – 0.3	MPa	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

