

XENOVTM RESIN X4830

REGION ASIA

DESCRIPTION

XENOV X4830 is a hydrostable, high modulus, low temperature ductile PC/PBT blend. Furthermore, this resin provides high chemical resistance, very low creep, low CTE, excellent fatigue and high heat dimensional stability. The X4830 could be positioned for body panels, safety equipment, housings, doorhandles, spring-loaded applications, medical device enclosures, outdoor sports equipment.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	60	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	60	MPa	ASTM D 638
Tensile Stress, yld, Type I, 5 mm/min	56	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	60	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4.1	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	140	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.5	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	150	%	ASTM D 638
Tensile Modulus, 5 mm/min	3400	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	96	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3100	MPa	ASTM D 790
Taber Abrasion, CS-17, 1 kg	30	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	55	MPa	ISO 527
Tensile Stress, break, 5 mm/min	60	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	61	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4.1	%	ISO 527
Tensile Strain, break, 5 mm/min	120	%	ISO 527
Tensile Strain, yield, 50 mm/min	4.2	%	ISO 527
Tensile Strain, break, 50 mm/min	110	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2900	MPa	ISO 178
Ball Indentation Hardness, H358/30	105	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched, 23°C	600	J/m	ASTM D 256
Izod Impact, notched, 0°C	150	J/m	ASTM D 256
Izod Impact, notched, -30°C	120	J/m	ASTM D 256
Multiaxial Impact	110	J	ISO 6603
Instrumented Impact Total Energy, 23°C	70	J	ASTM D 3763
Instrumented Impact Total Energy, -20°C	70	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*4 +23°C	45	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	15	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	9	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	40	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	12	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	133	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	125	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	106	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.2E-05	1/°C	ASTM E 831
Thermal Conductivity	0.2	W/m·°C	ISO 8302
CTE, -30°C to 80°C, flow	7.2E-05	1/°C	ISO 11359-2
CTE, -30°C to 80°C, xflow	9.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	133	°C	ISO 306
Vicat Softening Temp, Rate B/120	135	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	119	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	97	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.27	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.7 – 0.9	%	SABIC method
Melt Flow Rate, 266°C/5.0 kgf	7	g/10 min	ASTM D 1238
Density	1.27	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.42	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.14	%	ISO 62
Melt Volume Rate, MVR at 265°C/5.0 kg	6	cm³/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	90 – 100	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	255 – 270	°C	
Nozzle Temperature	250 – 265	°C	
Front - Zone 3 Temperature	250 – 270	°C	
Middle - Zone 2 Temperature	240 – 265	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	60 – 80	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

