

XENOYTM RESIN X4870HH

REGION AMERICAS

DESCRIPTION

XENOY X4870HH is a high heat, very high modulus and ductile PC/PET blend. Furthermore this resin provides chemical resistance, very low creep, low CTE, excellent fatigue and high heat dimensional stability. The X4870HH could be positioned for body panels, housings, medical device enclosures, outdoor sports equipment.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	65	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	50	MPa	ASTM D 638
Tensile Stress, yld, Type I, 5 mm/min	61	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	45	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	3.3	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	30	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3.7	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	60	%	ASTM D 638
Tensile Modulus, 5 mm/min	4600	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	104	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	4250	MPa	ASTM D 790
Taber Abrasion, CS-17, 1 kg	30	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	63	MPa	ISO 527
Tensile Stress, break, 5 mm/min	45	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	67	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.6	%	ISO 527
Tensile Strain, break, 5 mm/min	10	%	ISO 527
Tensile Strain, yield, 50 mm/min	3.8	%	ISO 527
Tensile Strain, break, 50 mm/min	10	%	ISO 527
Tensile Modulus, 1 mm/min	4300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	98	MPa	ISO 178
Flexural Modulus, 2 mm/min	4000	MPa	ISO 178
Ball Indentation Hardness, H358/30	105	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched, 23°C	90	J/m	ASTM D 256
Izod Impact, notched, 0°C	80	J/m	ASTM D 256
Izod Impact, notched, -30°C	70	J/m	ASTM D 256
Multiaxial Impact	90	J	ISO 6603
Instrumented Impact Total Energy, 23°C	60	J	ASTM D 3763
Instrumented Impact Total Energy, -20°C	60	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1A



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*4 -30°C	6	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	11	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	137	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	132	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	113	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.3E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.4E-05	1/°C	ASTM E 831
Thermal Conductivity	0.2	W/m·°C	ISO 8302
CTE, -30°C to 80°C, flow	4.8E-05	1/°C	ISO 11359-2
CTE, -30°C to 80°C, xflow	6.8E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	137	°C	ISO 306
Vicat Softening Temp, Rate B/120	139	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	131	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	113	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.34	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 266°C/5.0 kgf	8	g/10 min	ASTM D 1238
Density	1.34	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.42	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.14	%	ISO 62
Melt Volume Rate, MVR at 265°C/5.0 kg	7	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	265 – 275	°C	
Nozzle Temperature	260 – 275	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	250 – 275	°C	
Rear - Zone 1 Temperature	240 – 270	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.