

CYCOLOYTM FR RESINS CM6140

REGION AMERICAS

DESCRIPTION

CYCOLOY CM6140 Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) blend is an injection moldable, non chlorinated/brominated mineral-filled flame retardant grade. It features high modulus, good flow, ductility and low warpage. It has a UL94 V0@0.8mm and 5VB@1.5mm flame rating and is a good candidate for thin wall applications.

TYPICAL PROPERTY VALUES

Revision 20190924

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	65	MPa	ASTM D 638
Tensile Stress, yld, Type I, 5 mm/min	65	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	50	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	100	%	ASTM D 638
Tensile Modulus, 5 mm/min	3500	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	100	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3300	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.5	%	ISO 527
Tensile Strain, break, 50 mm/min	15	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	97	MPa	ISO 178
Flexural Modulus, 2 mm/min	3450	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	200	J/m	ASTM D 256
Izod Impact, notched, -30°C	88	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	50	J	ASTM D 3763
Izod Impact, notched 80*10*3 +23°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	5	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	10	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	5	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	91	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	83	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	97	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	89	°C	ASTM D 648
CTE, -40°C to 40°C, flow	5.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	5.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	98	°C	ISO 306



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/120	102	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	80	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.26	-	ASTM D 792
Water Absorption, 24 hours	0.1	%	ASTM D 570
Moisture Absorption, 50% RH, 24 hrs	0.01	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.3 – 0.5	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	17.5	g/10 min	ASTM D 1238
Density	1.25	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.09	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.01	%	ISO 62
Melt Volume Rate, MVR at 220°C/5.0 kg	14	cm³/10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	2.68E+16	Ohm-cm	ASTM D 257
Surface Resistivity	3.54E+15	Ohm	ASTM D 257
FLAME CHARACTERISTICS			
UL Recognized, 94V-1 Flame Class Rating	0.6	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	0.8	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	1.5	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	0.8	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	850	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	800	°C	IEC 60695-2-13
INJECTION MOLDING			
Drying Temperature	90	°C	
Drying Time	>4	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	275 – 300	°C	
Nozzle Temperature	280 – 300	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	275 – 300	°C	
Rear - Zone 1 Temperature	275 – 300	°C	
Mold Temperature	60 – 80	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

