

CYCOLOYTM FR RESINS CY5025

REGION ASIA

DESCRIPTION

CYCOLOY CY5025 Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) resin is a standard grade that can be injection molded. This non-chlorinated, non-brominated flame retardant PC/ABS has a UL V0 & 5VB flame rating. CYCOLOY CY5025 resin is a general purpose resin that is an excellent candidate for a wide variety of thin wall applications.

TYPICAL PROPERTY VALUES

Revision 20191009

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	59	MPa	SABIC - Japan Method
Tensile Stress, yld, Type I, 50 mm/min	56	MPa	ASTM D 638
Tensile Strain, break	79	%	SABIC - Japan Method
Tensile Strain, brk, Type I, 50 mm/min	99	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	89	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2570	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	57	MPa	ISO 527
Tensile Strain, break, 50 mm/min	99	%	ISO 527
Flexural Stress, yield, 2 mm/min	96	MPa	ISO 178
Flexural Modulus, 2 mm/min	2880	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	450	J/m	ASTM D 256
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	11	kJ/m ²	ISO 179/1eA
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	72	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.7E-05	1/°C	ASTM E 831
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	83	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	74	°C	ISO 75/Af
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Mold Shrinkage, flow, 1.5-3.2 mm	0.23	%	SABIC method
Mold Shrinkage, xflow, 1.5-3.2 mm	0.31	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	27	g/10 min	ASTM D 1238
Density	1.2	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.29	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+15	Ohm	ASTM D 257
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Compliant, 94V-1 Flame Class Rating	1	mm	UL 94 by SABIC-IP
UL Compliant, 94V-0 Flame Class Rating	1.2	mm	UL 94 by SABIC-IP
UL Compliant, 94-5VB Rating	1.5	mm	UL 94 by SABIC-IP
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	245 – 275	°C	
Nozzle Temperature	245 – 275	°C	
Front - Zone 3 Temperature	245 – 275	°C	
Middle - Zone 2 Temperature	220 – 265	°C	
Rear - Zone 1 Temperature	220 – 255	°C	
Mold Temperature	60 – 80	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

