



LNP™ STAT-KON™ Compound DEL36
Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound DCL-4036
Product reorder name: DEL36

LNP STAT-KON DEL36 is a compound based on Polycarbonate resin containing 30% Carbon Fiber, 15% PTFE. Added features include: Electrically Conductive, Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	1250	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	216300	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	1870	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	135600	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	123	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	0	%	ISO 527
Tensile Strain, break, 5 mm/min	1.5	%	ISO 527
Tensile Modulus, 1 mm/min	15740	MPa	ISO 527
Flexural Stress	193	MPa	ISO 178
Flexural Modulus, 2 mm/min	14390	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	48	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Multiaxial Impact	44	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	163	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	149	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	144	°C	ASTM D 648
CTE, -30°C to 30°C, flow	1.64E+01	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	3.72E+01	1/°C	ASTM D 696





LNP™ STAT-KON™ Compound DEL36

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	150	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	144	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.43	-	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.08	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.02 - 0.04	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.3 - 0.5	%	ASTM D 955
Density	1.43	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.12	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+00 - 4.E+00	Ohm	ASTM D 257





LNP™ STAT-KON™ Compound DEL36

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

