



LNP™ THERMOCOMP™ Compound MC004
Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound MC-1004
Product reorder name: MC004

LNP THERMOCOMP MC004 is a compound based on Polypropylene resin containing Carbon Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	48	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.5	%	ISO 527
Tensile Modulus, 1 mm/min	8100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	64	MPa	ISO 178
Flexural Stress, break, 2 mm/min	32	MPa	ISO 178
Flexural Modulus, 2 mm/min	7300	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	3.3E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.25E-04	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	129	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.05 - 0.25	%	SABIC Method
Density	1	g/cm ³	ISO 1183
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+04	Ohm	ASTM D 257





LNP™ THERMOCOMP™ Compound MC004

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	225 - 250	°C
Front - Zone 3 Temperature	240 - 250	°C
Middle - Zone 2 Temperature	215 - 225	°C
Rear - Zone 1 Temperature	195 - 205	°C
Mold Temperature	30 - 50	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

