



LNP™ THERMOCOMP™ Compound MF006S
Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound MFX-1006 HS
Product reorder name: MF006S

LNP THERMOCOMP MF006S is a compound based on Polypropylene resin containing 30% Glass Fiber. Added features of this material include: Heat Stabilized.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	820	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.8	%	ASTM D 638
Tensile Modulus, 50 mm/min	147600	kgf/cm ²	ASTM D 638
Flexural Stress	1330	kgf/cm ²	ASTM D 790
Flexural Modulus	63200	kgf/cm ²	ASTM D 790
Tensile Stress, break	80	MPa	ISO 527
Tensile Strain, break	3	%	ISO 527
Tensile Modulus, 1 mm/min	9120	MPa	ISO 527
Flexural Stress	135	MPa	ISO 178
Flexural Modulus	6800	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	61	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	37	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	157	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	133	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.84E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	4.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	6.9E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	4.4E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	161	°C	ISO 75/Bf





LNP™ THERMOCOMP™ Compound MF006S
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	141	°C	ISO 75/Af
PHYSICAL			
Density	1.12	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.6 - 0.8	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.9 - 1.1	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.65	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.98	%	ISO 294
Density	1.12	g/cm ³	ISO 1183





LNP™ THERMOCOMP™ Compound MF006S
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	225 - 250	°C
Front - Zone 3 Temperature	240 - 250	°C
Middle - Zone 2 Temperature	215 - 225	°C
Rear - Zone 1 Temperature	195 - 205	°C
Mold Temperature	30 - 50	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

