



LNP™ THERMOCOMP™ Compound MFB22S

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound MFX-1004 HS MG
Product reorder name: MFB22S

LNP THERMOCOMP MFB22S is a compound based on Polypropylene containing 10% Glass Fiber, 10% Glass Bead. Added feature of this grade is: Heat Stabilized.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	470	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	450	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3.2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4.1	%	ASTM D 638
Tensile Modulus, 5 mm/min	37300	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	740	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	28800	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.2	%	ISO 527
Tensile Strain, break, 5 mm/min	3.6	%	ISO 527
Tensile Modulus, 1 mm/min	3250	MPa	ISO 527
Flexural Stress	70	MPa	ISO 178
Flexural Modulus, 2 mm/min	2770	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	41	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
Multiaxial Impact	21	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	71	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	156	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D 648





LNP™ THERMOCOMP™ Compound MFB22S

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	148	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	103	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.04	-	ASTM D 792
Density	1.035	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.03	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	1 - 3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1 - 3	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62





LNP™ THERMOCOMP™ Compound MFB22S

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	225 - 250	°C
Front - Zone 3 Temperature	240 - 250	°C
Middle - Zone 2 Temperature	215 - 225	°C
Rear - Zone 1 Temperature	195 - 205	°C
Mold Temperature	30 - 50	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

