



# STAMAX™ 30YM240

PP LGF REINFORCED

## DESCRIPTION

STAMAX™ 30YM240 is a 30% long glass fiber reinforced grade. The glass fibres are chemically coupled to the PP matrix, resulting in high stiffness and strength.

IMDS ID: 16496906

## TYPICAL PROPERTY VALUES

Revision 20191025

| PROPERTIES                           | TYPICAL VALUES | UNITS | TEST METHODS |
|--------------------------------------|----------------|-------|--------------|
| POLYMER PROPERTIES                   |                |       |              |
| Density                              | 1120           | kg/m³ | ISO 1183     |
| Glass fibre content                  | 30             | %     | ISO 3451     |
| MECHANICAL PROPERTIES <sup>(1)</sup> |                |       |              |
| Tensile modulus                      |                |       |              |
| at 23 °C                             | 6600           | MPa   | ISO 527/1A   |
| at 80 °C                             | 4500           | MPa   | ISO 527/1A   |
| Tensile strength                     |                |       |              |
| at 23 °C                             | 105            | MPa   | ISO 527/1A   |
| at 80 °C                             | 60             | MPa   | ISO 527/1A   |
| Tensile elongation at break          |                |       |              |
| at 23 °C                             | 2.3            | %     | ISO 527/1A   |
| Flexural Modulus                     |                |       |              |
| at 23 °C                             | 6400           | MPa   | ISO 178      |
| at 80 °C                             | 4600           | MPa   | ISO 178      |
| Flexural strength                    |                |       |              |
| at 23 °C                             | 160            | MPa   | ISO 178      |
| at 80 °C                             | 95             | MPa   | ISO 178      |
| Charpy Impact Strength Notched       |                |       |              |
| at 23 °C                             | 20             | kJ/m² | ISO 179/1eA  |
| at -30 °C                            | 27             | kJ/m² | ISO 179/1eA  |
| Charpy impact unnotched              |                |       |              |
| at 23 °C                             | 60             | kJ/m² | ISO 179/1eU  |
| at -30 °C                            | 40             | kJ/m² | ISO 179/1eU  |
| THERMAL PROPERTIES                   |                |       |              |
| Heat deflection temperature          |                |       |              |
| at 1.80 MPa (HDT/A)                  | 158            | °C    | ISO 75/A     |
| Coeff. of linear thermal expansion   |                |       |              |
| -30 °C to 100 °C                     | 44             | µm/mK | ISO 11359-2  |

(1) All measurements on injection molded samples.





## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

