



SABIC® PPCOMPOUND 15T1040

PP COMPOUND MINERAL FILLED

DESCRIPTION

SABIC® PPcompound 15T1040 is a 40% talc-filled polypropylene homopolymer. The materials high fill grade makes for a very high stiffness. This combined with the good thermal stabilization makes it especially suited for applications requiring a very high modulus and high thermal stability.

SABIC® PPcompound 15T1040 is a designated automotive grade.

IMDS ID: 1648799

TYPICAL PROPERTY VALUES

Revision 20210715

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	6	dg/min	ISO 1133
Density ⁽¹⁾	1250	kg/m ³	ISO 1183
Filler content	40	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	0.9	%	SABIC method
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile			
stress at yield	36	MPa	ISO 527/1A
stress at break	26	MPa	ISO 527/1A
strain at break	17	%	ISO 527/1A
Flexural test			
Flexural modulus	3500	MPa	ISO 178/1A
Izod impact notched ⁽³⁾			
at 23 °C	2.5	kJ/m ²	ISO 180/1A
at 0 °C	1.6	kJ/m ²	ISO 180/1A
at -20 °C	1.4	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES ⁽¹⁾			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	130	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	65	µm/mK	ISO 11359-2

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.