



SABIC® PPCOMPOUND 55T1030

PP COMPOUND MINERAL FILLED

DESCRIPTION

SABIC® PPcompound 55T1030 is a Polypropylene copolymer with 30% talcum. It is especially suited for applications that require an exceptional stiffness combined with a high impact resistance (even at low temperatures) like dashboard carriers and other dashboard components that are exposed to high temperatures.

SABIC® PPcompound 55T1030 is a designated automotive grade.

IMDS ID: 16160823

TYPICAL PROPERTY VALUES

Revision 20211207

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 5 kg	20	dg/min	ISO 1133
at 230 °C and 2.16 kg	4	dg/min	ISO 1133
Density ⁽¹⁾	1130	kg/m³	ISO 1183
Filler content	30	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	1	%	SABIC method
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile			
Tensile modulus	2200	MPa	ISO 527/1A
stress at yield	24	MPa	ISO 527/1A
stress at break	18	MPa	ISO 527/1A
strain at break	80	%	ISO 527/1A
Flexural test			
Flexural modulus	2300	MPa	ISO 178/1A
Izod impact notched ⁽³⁾			
at 23 °C	13	kJ/m²	ISO 180/1A
at 0 °C	6	kJ/m²	ISO 180/1A
at -20 °C	3.5	kJ/m²	ISO 180/1A
THERMAL PROPERTIES ⁽¹⁾			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	120	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	65	µm/mK	ISO 11359-2

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break



STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.