



SABIC® PPCOMPOUND 55T1040

PP COMPOUND MINERAL FILLED
REGION AMERICAS

DESCRIPTION

SABIC® PPcompound 55T1040 is a general purpose, talc filled, heat stabilized copolymer polypropylene compound. This compound exhibits very high impact and high rigidity, and is suitable for injection molding applications.

IMDS ID: 278629571

TYPICAL PROPERTY VALUES

Revision 20211206

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 50 mm/min	20	MPa	ISO 527
Tensile Stress, break, 50 mm/min, 1A	14	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3	%	ISO 527
Tensile Strain, break, 50 mm/min	10.8	%	ISO 527
Tensile Modulus, 1 mm/min	2450	MPa	ISO 527
Flexural Modulus, 2 mm/min, 64mm span	3270	MPa	ISO 178
IMPACT			
Instrumented Impact Energy @ peak, 23°C @ 2.2 m/s	10	J	ASTM D3763
Izod Impact, notched, 23°C, 80*10*4mm, Cut	7	kJ/m ²	ISO 180/1A
Izod Impact, notched, -30°C, 80*10*4mm, Cut	2	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C, 80*10*4mm, Cut	8	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, -30°C, 80*10*4mm, Cut	2	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening 10N, 50°C/hr	142	°C	ISO 306
HDT 0.45 MPa, 80*10*4mm, Cut	70	°C	ISO 75-1&2
HDT 1.8 MPa, 80*10*4mm, Cut	124	°C	ISO 75-1&2
PHYSICAL			
Specific Gravity	1.27	-	ASTM D792
Density	1.27	g/cm ³	ISO 1183
Melt Flow Rate, 230°C/2.16 kg	3	g/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	80 – 100	°C	
Drying Time	2 – 4	Hrs	
Melt Temperature	210 – 270	°C	
Nozzle Temperature	210 – 270	°C	
Front - Zone 3 Temperature	210 – 270	°C	
Middle - Zone 2 Temperature	200 – 250	°C	
Rear - Zone 1 Temperature	190 – 230	°C	
Mold Temperature	15 – 60	°C	
Back Pressure	1 – 1.5	MPa	





STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

