

# SABIC® PPCOMPOUND F9007

PP COMPOUND MINERAL FILLED IMPACT MODIFIED

## DESCRIPTION

Preliminary datasheet

SABIC® PPcompound F9007 is an elastomer-modified mineral filled Polypropylene for automotive interior applications. This material has been designed to combine a good performance profile with good processing. This material is designed for intended use in foamed interior applications. Datasheet values are based on standard, solid specimen.

SABIC® PPcompound F9007 is a designated automotive grade.

IMDS ID: 963556160

## TYPICAL PROPERTY VALUES

Revision 20210323

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 230 °C and 2.16 kg	28	dg/min	ISO 1133
<b>Density</b> <sup>(1)</sup>	955	kg/m³	ISO 1183
<b>Filler content</b>	7	%	SABIC method
<b>Mould shrinkage</b> <sup>(2)</sup>			
24 hours after injection moulding	1.4	%	SABIC method
<b>MECHANICAL PROPERTIES</b> <sup>(1) (3)</sup>			
<b>Tensile</b>			
Tensile modulus	1850	MPa	ISO 527/1A
stress at yield	28	MPa	ISO 527/1A
stress at break	20	MPa	ISO 527/1A
strain at break	5	%	ISO 527/1A
<b>Flexural test</b>			
Flexural modulus	1850	MPa	ISO 178/1A
<b>Izod impact notched</b> <sup>(4)</sup>			
at 23 °C	6	kJ/m²	ISO 180/1A
<b>THERMAL PROPERTIES</b> <sup>(1)</sup>			
<b>Heat deflection temperature</b>			
at 1.8 MPa (HDT/A)	58	°C	ISO 75
at 0.45 MPa (HDT/B)	102	°C	ISO 75
<b>Coeff. of linear thermal expansion</b>			
-30 °C to 100°C	95	µm/mK	ISO 11359-2

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

(4) U-shaped notch; N.B.: No Break



## STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

