

SABIC® PPCOMPOUND G1620B

PP SHORT GLASS FIBER REINFORCED

DESCRIPTION

SABIC®PPcompound G1620B is a low flow PP random co-polymer with glass fibers for multi-layer PPR-GF composite pipe applications. This material has been designed to combine good performance properties with good processing and excellent surface esthetics.

SABIC®PPcompound G1620B is a designated pipe grade.

TYPICAL PROPERTY VALUES

Revision 20230421

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	0.3	dg/min	ISO 1133
Density⁽¹⁾	1030	kg/m ³	ISO 1183
Filler content	20	%	SABIC method
MECHANICAL PROPERTIES⁽¹⁾			
Tensile test			
Tensile modulus	3200	MPa	ISO 527/1A
stress at break	45	MPa	ISO 527/1A
strain at break	7	%	ISO 527/1A
Flexural test			
Flexural modulus	2800	MPa	ISO 178
Izod impact notched⁽²⁾			
at 23 °C	17	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES⁽¹⁾			
Heat deflection temperature			
at 1.80 MPa (HDT/A)	-	°C	ISO 75/A
at 0.45 MPa (HDT/B)	-	°C	ISO 75/B
Coeff. of linear thermal expansion			
-30 °C to 100 °C	-	μm/mK	ISO 11359-2

(1) Injection molded sample ISO527-1A

(2) N.B.: No Break

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

