



SABIC® PPCOMPOUND H1025

FLAME RETARDANT GLASS FIBER REINFORCED POLYPROPYLENE

DESCRIPTION

SABIC®PPcompound H1025 is a good flow, halogen free flame retardant, homopolymer with 25% glass fiber, developed for E&E and automotive injection molded applications. It has a UL94V0@1.5mm and 5VA@3.0mm flame rating. This material has been designed to combine a good performance profile with good processing and FR characteristics.

IMDS ID: 712120282
UL Yellow Card: E111275

TYPICAL PROPERTY VALUES

Revision 20230801

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	9	dg/min	ISO 1133
Density ⁽¹⁾	1230	kg/m ³	ISO 1183
Filler content	25	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	0.75	%	SABIC method
MECHANICAL PROPERTIES ^{(1) (3)}			
Tensile			
Tensile modulus	7600	MPa	ISO 527/1A
stress at yield	No Yield	MPa	ISO 527/1A
stress at break	91	MPa	ISO 527/1A
strain at break	3	%	ISO 527/1A
Flexural test			
Flexural modulus	7300	MPa	ISO 178/1A
Izod impact notched ^{(1) (3)}			
at 23 °C	7	kJ/m ²	ISO 180/1A
at 0 °C	6	kJ/m ²	ISO 180/1A
at -20 °C	5	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES			
Heat deflection temperature			
at 1.8 MPa (HDT/A) ⁽¹⁾	146	°C	ISO 75
at 0.45 MPa (HDT/B) ⁽¹⁾	158	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100°C	50	µm/mK	ISO 11359-2
FLAMMABILITY PROPERTIES			
Comparative Tracking Index	600	V	IEC 60112
UL94			
Lowest thickness V0	1.5	mm	UL 94
GWFI			
at 1.6 mm	960	°C	IEC 60695-2-13
GWIT			



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
at 0.8 mm	825	°C	IEC 60695-2-13

- (1) Injection molded sample ISO527-1A
(2) Injection molded plaque 65x65x3.2mm
(3) N.B.: No Break

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.