



# SABIC® PPCOMPOUND T2E-3320EH

PP COMPOUND MINERAL FILLED

## DESCRIPTION

SABIC® PPcompound T2E-3320EH is a Polypropylene compound, which is formulated with 25 wt% recycled plastics. The grade is part of SABIC's TRUCIRCLE™ portfolio and services. High stiffness, combined with good thermal stabilization and excellent emission performance, makes the grade suited for use in applications at elevated temperatures and emission requirements. SABIC® PPcompound T2E-3320EH is a designated automotive grade. For SABIC®PPcompound T2E-3320EH either PCR or PIR material is used. In case PCR is used IMDS ID: 1092210969 or in case PIR is used IMDS ID: 1062971409

SABIC® PPcompound T2E-3320EH is a designated automotive grade.

## TYPICAL PROPERTY VALUES

Revision 20230727

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 230 °C and 2.16 kg	28	dg/min	ISO 1133
<b>Density <sup>(1)</sup></b>	1040	kg/m³	ISO 1183
<b>Filler content</b>	20	%	SABIC method
<b>Mould shrinkage <sup>(2)</sup></b>			
24 hours after injection moulding	1.1	%	SABIC method
<b>MECHANICAL PROPERTIES <sup>(1)</sup></b>			
<b>Tensile test</b>			
Tensile modulus	2600	MPa	ISO 527/1A
stress at yield	29	MPa	ISO 527/1A
stress at break	25	MPa	ISO 527/1A
strain at break	10	%	ISO 527/1A
<b>Flexural test</b>			
Flexural modulus	2700	MPa	ISO 178/1A
<b>Izod impact notched <sup>(3)</sup></b>			
at 23 °C	2.5	kJ/m²	ISO 180/1A
at 0 °C	2.0	kJ/m²	ISO 180/1A
at -20 °C	1.5	kJ/m²	ISO 180/1A
<b>THERMAL PROPERTIES <sup>(1)</sup></b>			
<b>Heat deflection temperature</b>			
at 0.45 MPa (HDT/B)	117	°C	ISO 75
<b>Coeff. of linear thermal expansion</b>			
-30 °C to 100 °C	100	µm/mK	ISO 11359-2

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

## STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™





## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

