

SABIC® PP QR6731K

POLYPROPYLENE RANDOM COPOLYMER

DESCRIPTION

SABIC® PP QR6731K is specially developed for producing injection molded & ISBM articles with very high clarity at low processing temperatures. This grade contains advance clarifier and anti-static agent.

SABIC® PP QR6731K has following features: Consistent processability; Good stiffness; Exceptional clarity; Lower energy consumption and less cycle time due to low processing temperatures.

TYPICAL APPLICATIONS

SABIC® PP QR6731K can be used for clear housewares items, caps & closures, food containers, bottles (ISBM), lids and CD boxes.

TYPICAL PROPERTY VALUES

Revision 20190327

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate at 230 °C and 2.16kg	25	g/10 min	ASTM D1238
Density at 23°C	905	kg/m ³	ASTM D790
MECHANICAL PROPERTIES⁽¹⁾			
Tensile Properties Strength @ Yield	28	MPa	ASTM D 638
Elongation @ Yield	12	%	ASTM D 638
Flexural Modulus (1% Secant) ⁽¹⁾	1050	MPa	ASTM D790 A
Izod Impact Strength notched, at 23°C	65	J/m	ASTM D256
Rockwell Hardness, R-Scale	94	-	ASTM D785
THERMAL PROPERTIES			
Vicat Softening Temperature	127	°C	ASTM D1525
Heat deflection temperature at 455kPa	83	°C	ASTM D648

(1) Based on injection molded specimens

PROCESSING CONDITIONS

Typical processing conditions for QR6731K are:

Barrel temperature range: 190 - 220°C

Mold Shrinkage: 1.2 - 2.0% depending on wall thickness and processing conditions.

Mold Temperature: Normally 15 - 40°C, up to 65°C for thick parts.

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>. For additional specific information please contact SABIC local representative.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical / medical applications.

© 2019 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.