

SABIC® PP QR681K

PP RANDOM COPOLYMER QRYSTAL

DESCRIPTION

SABIC® PP QR681K is a new highly transparent random copolymer grade in the blow moulding product range. Impact, transparency, stiffness are well balanced and give you the opportunity to make weight optimized blow moulding products. This grade combines improved aesthetics of the finished articles with low temperature processability. Part aesthetics are not affected by the lower temperatures, providing for a broader operating window. High transparency, contact clarity and gloss will produce appealing blow moulded bottles. These properties, combined with a high heat deflection temperature, result in a wide variety of applications where the SABIC® PP QR681K can be used.

Application:

SABIC® PP QR681K is used for various blow moulding processes like Extrusion Blow Moulding and Injection (Stretch) Blow Moulding. SABIC® PP QR681K applications range from household to personal care products, but the material is also very suited for food packaging where a high heat distortion could be required.

Health, Safety and Food Contact regulations: Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com> The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

TYPICAL PROPERTY VALUES

Revision 20181123

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	2.2	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
FORMULATION			
Clarified	✓	-	-
MECHANICAL PROPERTIES			
Tensile test			
stress at yield ⁽¹⁾	26	MPa	ISO 527-2 1A
tensile modulus ⁽²⁾	950	MPa	ISO 527-2 1A
strain at yield	13	%	ISO 527-2 1A
Izod impact notched			
at 23 °C	8	kJ/m ²	ISO 180/1A
Charpy Impact Strength Notched			
at 23 °C	8	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Heat deflection temperature ⁽³⁾			
at 0.45 MPa (HDT/B)	65	°C	ISO 75/B

(1) Speed of testing: 50 mm/min

(2) Speed of testing: 1 mm/min

(3) Flat wise (testbar 80*10*4mm)

QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.