



## LNP™ LUBRICOMP™ Compound AL003

### Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound AL-4030

Product reorder name: AL003

LNP LUBRICOMP\* AL003 is a compound based on Acrylonitrile Butadiene Styrene resin containing PTFE. Added features of this material include: Internally Lubricated.

TYPICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	Unit	Standard
<b>MECHANICAL</b>			
Tensile Stress, yield	360	kgf/cm <sup>2</sup>	ASTM D 638
Tensile Stress, break	330	kgf/cm <sup>2</sup>	ASTM D 638
Tensile Strain, yield	2.3	%	ASTM D 638
Tensile Strain, break	14.7	%	ASTM D 638
Tensile Modulus, 50 mm/min	24600	kgf/cm <sup>2</sup>	ASTM D 638
Flexural Stress	630	kgf/cm <sup>2</sup>	ASTM D 790
Flexural Modulus	21000	kgf/cm <sup>2</sup>	ASTM D 790
Tensile Stress, yield	35	MPa	ISO 527
Tensile Stress, break	32	MPa	ISO 527
Tensile Strain, yield	2.7	%	ISO 527
Tensile Strain, break	11.6	%	ISO 527
Tensile Modulus, 1 mm/min	2280	MPa	ISO 527
Flexural Stress	61	MPa	ISO 178
Flexural Modulus	2000	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	20	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	116	cm-kgf	ASTM D 3763
Multiaxial Impact	83	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	21	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
<b>PHYSICAL</b>			
Density	1.13	g/cm <sup>3</sup>	ASTM D 792

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA



## LNP™ LUBRICOMP™ Compound AL003

### Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	Unit	Standard
<b>PHYSICAL</b>			
Moisture Absorption, 50% RH, 24 hrs	0.2	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.6 - 0.8	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.8 - 1	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.6 - 0.8	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.8 - 1	%	ISO 294
Density	1.13	g/cm <sup>3</sup>	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.31	%	ISO 62

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.